

GREAT JOB
GREAT SOLUTIONS

Selsil

Selsil[®]



Selsil stands out as one of the leading manufacturers of construction and automotive chemicals in the EMEA region, operating with two state-of-the-art production facilities located in Silivri and Çorlu, Turkey.



The Silivri facility, built on a total area of 33,000 m² with 25,000 m² of enclosed production space, and the Çorlu aerosol production plant, established on a 46,000 m² site with 19,000 m² of enclosed space, together provide Selsil with an exceptional and ever-expanding production capacity.



Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).

Wheelmark



Nonfood Compounds (S2)

UK
CA

ISO 9001/OHSAS 18001
ISO 14001/ISO 27001



CE

TABLE OF CONTENTS

CLEANING PRODUCTS

CLEANERS

- 9 PAK General Purpose Cleaner
- 10 PAK Foam Cleaner

SEALANTS PRODUCTS

SILICONES

- 12 Multi Purpose Silicone 280g
Multi Purpose Silicone 280ml & 50ml
- 13 Multi Purpose Silicone 310ml
Kitchen & Bathroom Silicone
- 14 Exterior Neutral Silicone
Aquarium Silicone
- 15 RTV High-Temperature Silicone
X-Heat Silicone
- 16 Pro Silicone
Mirror Silicone
- 17 Fire Stop Silicone
Auto-Sel Gasket Silicone

ACRYLICS

- 18 Acrylic Sealant
Silicone Acrylic Sealant
- 19 Exterior Siliconized Acrylic
Silicone Sealant
- 20 Acrylic Skirting Adhesive
Fire Stop Acrylic

HYBRIDS

- 21 X1
Mirror Adhesive
- 22 Ultra Clear Crystal Transparent Adhesive
Ultra Tack Strong Adhesive

POLYURETHANES

- 23 Water Stop Liquid Membrane
- 24 PU 25
PU 40
- 25 PU 50
PU 60

Selsil[®]

MARINE PRODUCTS

MARINE

- 27 Marine Deck Sealant
Marine Bedding Adhesive
- 28 PU Marine Grade Adhesive
Teak Cleaner Spray

POLYURETHANE FOAMS

FILLING AND ADHESIVE

- 30 Polyurethane Foam (Manual) 750g Gross
Polyurethane Foam (Gun) 750g Gross
- 31 Polyurethane Foam (Manual) 845g
Polyurethane Foam (Gun) 845g
- 32 PU Adhesive Insulation Foam (Manual)
PU Adhesive Insulation Foam (Gun)
- 33 Fast-Curing Adhesive Foam (Gun)
Thermal and Acoustik Spray Foam
- 34 Stone & Brick Adhesive Foam (Gun)
Low Expansion Foam (Gun)
- 35 B1 Fire-Resistant Foam (Manual)
B1 Fire-Resistant Foam (Gun)
- 36 Dual-Valve Foam
Reusable Safety Valve Foam
- 37 Mega Foam (Gun)
Foam Cleaner

ADHESIVES

MONTAGE

- 39 Fire Sealant
PU D4 Express Adhesive
- 40 Montage Kit
D3 Wood Glue

Selsil[®]

EPOXIES

- 41 Multi Purpose Epoxy Putty
Plastic Epoxy Putty
- 42 Wood Epoxy Putty
Steel Epoxy Putty
- 43 Epoxy Adhesive 5 Minutes
Waterproof Adhesive 30 Minutes
- 44 Metal Adhesive 5 Minutes
Plastic Welding
- 45 Aqua Epoxy Putty

CYANOACRYLATE

- 46 NINJA Super Glue
Super Glue With Activator

MULTI PURPOSE

- 47 Multi-Purpose Adhesive Spray

BAND

- 48 Emergency Aid Band

DIY

- 49 Contact Adhesive
Clear Glue

HARD PVC ADHESIVE

- 50 P12 Adhesive For PVC Pipes

MARBLE AND GRANITE ADHESIVE

- 51 Marble and Granite Adhesive

EPDM ADHESIVE

- 52 EPDM Adhesive

CHEMICAL ANCHORS

- 54 Epoxy-Based
Polyester-Based

Selsil[®]

SPRAYS

TECHNICAL SPRAY

- 56 Brake Cleaner
 - Rust Remover
 - Label Remover Spray
 - Liquid Grease Spray
- 57 Silicone Spray
 - Zinc Spray
 - Engine Cleaner
 - Gasket Cleaner
- 58 Mag Welding Spray (Silicone-Free)
 - Welding Spray (Silicone-Free)
 - Mold Release Spray (Silicone-Free)
 - Mold Release Spray
- 59 Belt Dressing
 - Carburetor Cleaner
 - Air Conditioning Cleaner
 - Cockpit Shiner
- 60 Rubber Seals Renovation
 - Contact Cleaner
 - Tar & Pitch Cleaner
 - Seat Belt Lubricant Cleaner
- 61 Ether Car Starter
 - Mold Cleaner
 - Tire Shine
 - Electronic Card Cleaning Spray (Oil Free)
- 62 Rust Remover Pro
 - Pro Cobra Head
 - Non-Flammable Industrial Cleaning Spray

ACRYLIC SPRAY PAINT

- 63 Rainbow Spray Gas
 - Rainbow Fluorescent Paint
- 64 Rainbow Colors Spray Paint

Selsil[®]

CLEANING

Selsil[®]

PAK GENERAL PURPOSE CLEANER

PROPERTIES

Selsil PAK is a super cleaning paste ideal for cleaning all domestic and non-domestic surfaces. Perfectly clean. Removes grease and dirt. Detergent components of natural origin. Easy to use, with excellent results.

APPLICATIONS

Thanks to its powerful formulation all stains and rust on pots, barbecues, ceramic tiles, glass, sinks, PVC, garden furniture, paints, boats, hobs will be gone in a minute.

USE

Pour some Selsil PAK on the stained and dirty surface and rub with the help of a clean cloth. After rubbing, rinse with water. Do not use on plastic, painted wood and aluminum parts. Do not use the product on hands, face and on surfaces that could come into direct contact with food. Do not use directly on hot surfaces. Do not exert excessive pressure on glass and ceramic hobs as the surface could be scratched.

NO STAINS NO RINGS. LONG LASTING.



Content



500 gr

12 Pcs

PAK FOAM CLEANER

PROPERTIES

With its superior-performance foamy formula, Selsil Pak Miracle Cleaning Spray can easily clean and remove even the most stubborn and challenging oils on vertical surfaces just in seconds.

APPLICATIONS

It can be used for cleaning dirt and oils on the surface of cooking hobs, ovens, exhaust fans, cooker hoods, cooker hood filters, kitchen countertops, exhaust fans, kitchen cupboards and bathroom cabinets, marble, tile and ceramic surfaces, stainless steel and aluminium surfaces, sheet and other metal surfaces, oven trays, pans and cooking pots, PVC and plastic surfaces, bicycle, motorcycle and automobile rims, MDF tables, leather, vinyl and canvas shoes, all painted surfaces, glass surfaces, leather seats and upholstery, faucets and sinks.

USE

General Usage Method: Spray Selsil Pak Cleaning Spray on the dirty surface, wait for a while and then wipe it with a sponge or cloth. For surfaces with stubborn, challenging and excessive amounts of dirt repeat the foregoing step.

NO STAINS NO RINGS. LONG LASTING.



Content



500 ml

12 Pcs

SEALANTS

Selsil[®]

SILICONES

MULTI PURPOSE SILICONE

PROPERTIES

Selsil Universal Silicone is a one-component acetic drying silicone sealant, suitable for sealing in general. It has a very strong adhesion and can be used on the most common non porous building materials.

- Remains permanently elastic even after hardening. Excellent adhesion on non-porous surfaces. Resists aging and does not discolor.
- Resists a wide range of cleaning chemicals.
- Can be applied in all seasons.
- Sealing of electrical and telephone devices, sockets and switches.

APPLICATIONS

Ideal for general sealing applications.

- Sealing of doors and windows.
- Suitable for DIY. Bathrooms, kitchens and plumbing systems.
- Connections and expansion joints on glass, porcelain, steel, etc.
- Sealing of electrical and telephone devices, sockets and switches



TECHNICAL DATA

| | |
|-------------------------|-------------------------------|
| Base | Silicone Polymer |
| Polymerization system | Acetic |
| Density | 0.91-0.97g/ml - (ASTM D 792) |
| Hardness | 10-15 (After 28 Days) |
| Tack-free time | 11-12 min. (23°C and 50% R.H) |
| Cure rate | Min. 2mm/ 24h(23°C e 50% R.H) |
| Tensile strength | 1,1 N/mm2 - (ASTM D 412) |
| Elongation at break | ≥350% - (ASTM D 412) |
| Sagging | 0 mm - (ISO 7390) |
| Application temperature | : +5°C to +40°C |

| Ral | Content | |
|-------|---------|--------|
| Clear | 280 gr | 25 Pcs |
| White | 280 gr | 25 Pcs |
| Black | 280 gr | 25 Pcs |

MULTI PURPOSE SILICONE

PROPERTIES

Selsil Universal Silicone is a one-component acetic drying silicone sealant, suitable for sealing in general. It has a very strong adhesion and can be used on most common non porous building materials.

- Remains permanently elastic even after hardening. Excellent adhesion on non porous surfaces. Resists aging and does not discolor.
- Resists a wide range of cleaning chemicals.
- Can be applied in all seasons.

APPLICATIONS

Ideal for general sealing applications.

- Sealing of doors and windows.
- Suitable for DIY. Bathrooms, kitchens and plumbing systems.
- Connections and expansion joints on glass, porcelain, steel, etc.
- Sealing of electrical and telephone devices, sockets and switches



TECHNICAL DATA

| | |
|-------------------------|----------------------------------|
| Base | Silicone Polymer |
| Polymerization system | Acetic |
| Density | 0.91-0.97 g/ml - (ASTM D 792) |
| Hardness | 15-20 Shore A (After 28 Days) |
| Tack-free time | 10 - 15 min. (23°C and 50% R.H) |
| Cure rate | Min. 2 mm/ 24 h (23°C e 50% R.H) |
| Tensile strength | 1.8 N/mm2 - (ASTM D 412) |
| Elongation at break | ≥350% - (ASTM D 412) |
| Sagging | 0 mm - (ISO 7390) |
| Application temperature | : +5°C to +40°C |

| Ral | Content | |
|--------------|---------|--------|
| Clear | 280 ml | 25 Pcs |
| White | 280 ml | 25 Pcs |
| Black | 280 ml | 25 Pcs |
| Champagne | 280 ml | 25 Pcs |
| Golden Oak | 280 ml | 25 Pcs |
| Alü Gray | 280 ml | 25 Pcs |
| Ant Gray | 280 ml | 25 Pcs |
| Bahama Beige | 280 ml | 25 Pcs |
| Brown | 280 ml | 25 Pcs |

SILICONES

MULTI PURPOSE SILICONE

PROPERTIES

Selsil Universal Silicone is a one-component acetic drying silicone sealant, suitable for sealing in general. It has a very strong adhesion and can be used on the most common non porous building materials.

- Remains permanently elastic even after hardening. Excellent adhesion on non-porous surfaces. Resists aging and does not discolor.
- Resists a wide range of cleaning chemicals.
- Can be applied in all seasons.
- Sealing of electrical and telephone devices, sockets and switches.

APPLICATIONS

Ideal for general sealing applications.

- Sealing of doors and windows.
- Suitable for DIY. Bathrooms, kitchens and plumbing systems.
- Connections and expansion joints on glass, porcelain, steel, etc.
- Sealing of electrical and telephone devices, sockets and switches



KITCHEN & BATHROOM SILICONE

PROPERTIES

Selsil Kitchen and Bathroom Silicone is a high performance acetic cure silicone sealant designed for filling and sealing spaces in a wide range of sanitary applications.

- Does not change color over time.
- Exceptional resistance to mold and mildew.
- Resists extreme temperatures and aging.
- Does not crack and does not lose color.
- Resists detergents, cleaners and chemicals in general.
- Acetic hardening system.
- Anti mold.

APPLICATIONS

Joints on sanitary fittings and seals in kitchens and bathrooms.

- Sealing of joints, windows and weatherproof systems



TECHNICAL DATA

| Base | Silicone Polymer |
|-------------------------|------------------------------------|
| Polymerization system | |
| Density | 0.93-0.99 g/ml(TS 781-ISO 758) |
| Hardness | 16-17 Shora A (After 28 Days) |
| Tack-free time | 11-12 min. (23°C and 50% R.H) |
| Cure rate | Min 2 mm/24 h |
| Tensile strength | 2 N/mm ² - (ASTM D 412) |
| Elongation at break | ≥350% - (ASTM D 412) |
| Sagging | 0 mm - (ISO 7390) |
| Application temperature | :+5°C to +40°C |

TECHNICAL DATA

| Base | Silicone Polymer |
|-------------------------|----------------------------------|
| Polymerization system | Acetic |
| Density | 1.02 +- 0.03g/ml(TS 781-ISO 758) |
| Hardness | 16-17(After 28 Days) |
| Tensile strength | 1,5 N/mm ² (ISO 8339) |
| Tack-free time | 12 min (23 oC, 50% RH) |
| Cure rate | Min 2 mm/24 h |
| Elongation at break | ≥300% - (ASTM D 412) |
| Elastic recovery | Approx 100% |
| Sagging | 0 mm (ISO 7390) |
| Volume loss | <10% (ISO 10563) |
| Temperature resistance | -45°C to +150°C |
| Application temperature | +5°C to +40°C |

| Ral | Content | |
|------------|---------|--------|
| Clear | 310 ml | 25 Pcs |
| White | 310 ml | 25 Pcs |
| Black | 310 ml | 25 Pcs |
| Golden Oak | 310 ml | 25 Pcs |

| Ral | Content | |
|-------|---------|--------|
| Clear | 280 ml | 25 Pcs |
| | 50 ml | 12 Pcs |
| White | 280 ml | 25 Pcs |

SILICONES

EXTERIOR NEUTRAL SILICONE

PROPERTIES

Selsil Neutral Silicone for Constructions and Sheet Metal is a neutral polymerization silicone product. Offers high performance and is formulated for filling and sealing applications in a wide range of building materials. Has exceptional adhesive power, odorless and non-corrosive. 100% silicone, solvent-free.

- One-component, moisture-hardening.
- Excellent adhesion on a wide range of porous and non-porous materials.
- Excellent resistance to atmospheric agents, direct sunshine, rain, snow and ozone.
- Fast polymerization.
- Low modulus, high elasticity.

APPLICATIONS

- Sealing in sheet metal work, for flashings, copper, steel and galvanized sheet metal gutters, connection joints (walls, concrete, PVC, wood, glass).
- Installation of windows, doors and glass.
- Sealing in kitchens and bathrooms or where almost total absence of odor is required.

TECHNICAL DATA

| | |
|-------------------------|---|
| Base | Silicone Polymer (Oxime) |
| Polymerization system | Neutra |
| Density | 0,98 ± 0,03 g/ml - (ASTM D 792) |
| Density | 1,40 ± 0.03 g/ml - (ASTM D 792) |
| Hardness | 15-20 Shore A (trans. and alu.) (after 28 days) |
| Hardness | 25-30 Shore A (colors)(after 28 days) |
| Tack-free time | 12 min (23 oC, 50% RH) |
| Cure rate | Min 2 mm/24 h |
| Tensile Strength | 1.3 N/mm ² |
| Elongation at break | ≥250% (ASTM D412) |
| Sagging | 0 mm (ISO 7390) |
| Temperature resistance | -50°C to +150 °C |
| Application temperature | +5°C to +40°C |

| Ral | Content | Content | Content |
|-----|----------------------|---------|---------------|
| | Clear 300 ml | 25 Pcs | 600 ml 20 Pcs |
| | Black 300 ml | 25 Pcs | 600 ml 20 Pcs |
| | White 300 ml | 25 Pcs | |
| | Gray 300 ml | 25 Pcs | |
| | Golden Oak 300 ml | 25 Pcs | |
| | Alü Gray 300 ml | 25 Pcs | |
| | Ant. Gray 300 ml | 25 Pcs | |
| | Concrete Gray 300 ml | 25 Pcs | |
| | Pearl Bej 300 ml | 25 Pcs | |
| | Brown 300 ml | 25 Pcs | |



AQUARIUM SILICONE

PROPERTIES

Selsil Aquarium Silicone has been specifically formulated for the fabrication of fresh and salt-water aquariums. The bonds are unaffected by continuous immersion in water and, when fully cured, is non-toxic to fish.

- 100% silicone polymer
- High strength
- Solvent free
- Resistant to ozone, ultra violet radiation and temperature extremes

APPLICATIONS

- Contact area must be dry, clean, free from dust, oil and grease.
- Ensure neat sealant edges mask the areas adjacent to joints with masking tape.
- Cut the tip of the cartridge with angle in accordance with size of the surface to be applied on.
- Place the cartridge in the gun and inject the joint with the sealant.
- The applied sealant should be smoothed immediately with a wet spatula, tool or finger.
- Remove masking tape right after smoothing.

TECHNICAL DATA

| | |
|-------------------------|------------------------|
| Base | Silicone Polymer |
| Polymerization system | Acetic |
| Density | 1.02±0.03 g/ml |
| Hardness | 15 ± 3 Shore A |
| Tack-free Time | 12 min. |
| Cure Rate | 2mm |
| Tensile Strength | 1.50 N/mm ² |
| Elongation at break | >500 |
| Temperature resistance | -45 °C to +150 °C |
| Application temperature | +5°C to +40°C |
| Sagging | 0mm |

| Ral | Content | Content |
|-----|--------------|---------|
| | Clear 280 ml | 25 Pcs |



SILICONES

RTV HIGH TEMPERATURE SILICONE

PROPERTIES

Selsil RTV High Temperature Silicone, one-component, moisture-cure, acetoxy-based silicone.

- 100% silicone polymer
- High strength
- Solvent free
- Compliant with ISO 11600 - F&G - 25 HM
- Resistant to UV rays
- Resistant up to between -50°C and +250°C

APPLICATIONS

- Contact area must be dry, clean, free from dust, oil and grease.
- Ensure neat sealant edges mask the areas adjacent to joints with masking tape.
- Cut the tip of the cartridge with angle in accordance with size of the surface to be applied on.
- Place the cartridge in the gun and inject the joint with the sealant.
- The applied sealant should be smoothed immediately with a wet spatula, tool or finger.
- Remove masking tape right after smoothing.



TECHNICAL DATA

| | |
|-------------------------|------------------------|
| Base | Silicone Polymer |
| Polymerization system | Acetic |
| Density | 1.02±0.03 g/ml |
| Hardness | 15 ± 3 Shore A |
| Tack-free Time | 12 min. |
| Cure Rate | 2mm |
| Tensile Strength | 1.50 N/mm ² |
| Elongation at break | >500 |
| Temperature resistance | -45 °C to +150 °C |
| Application temperature | +5°C to +40°C |
| Sagging | 0mm |

| Ral | Content | |
|-----|---------|---------------|
| | Red | 280 ml 25 Pcs |
| | | 50 ml 48 Pcs |
| | Black | 50 ml 48 Pcs |

X HEAT SILICONE

PROPERTIES

Selsil X Thermal Silicone is a silicone sealant developed for sealing, bonding and repairing applications where heat resistance is required.

Once cured, it is an acetic silicone that provides permanent heat resistance up to 150°C.

APPLICATIONS

- Gaskets and bonding in the automotive industry.
- Sealing in heating systems and ovens.



TECHNICAL DATA

| | |
|-------------------------|---------------------------------|
| Base | Silicone Polymer |
| Polymerization system | Acetic |
| Density | 0.96±0.03 g/ml (TS 781 ISO 758) |
| Hardness | 16-17 Shore A |
| Tack-free Time | 11-12 dk (23°C ve 50% R.H) |
| Cure Rate | 2 mm/gün |
| Tensile Strength | 1.5 N/mm ² |
| Elongation at break | ≥350% - (ASTM D 412) |
| Temperature resistance | 0 mm - (ISO 7390) |
| Application temperature | : +5°C ile +40°C |

| Ral | Content | |
|-----|---------|---------------|
| | Red | 280 ml 25 Pcs |

SILICONES

PRO SILICONE

PROPERTIES

Selsil Pro is a one-component acetoxy based silicone sealant. It is used as a filling and bonding material for ceramic tile, window, aluminium, metal in bathroom and kitchen.

- 100 % silicone polymer.
- Excellent elasticity.
- Solvent free.
- Resistant to moisture Resistant to UV

APPLICATIONS

- Contact area must be dry, clean, free from dust, oil and grease.
- Ensure neat sealant edges mask the areas adjacent to joints with masking tape.
- Cut the tip of the cartridge with angle in accordance with size of the surface to be applied on.
- Place the cartridge in the gun and inject the joint with the sealant
- The applied sealant should be smoothed immediately with a wet spatula, tool or finger.
- Remove masking tape right after smoothing.



MIRROR SILICONE

PROPERTIES

High-performance neutral-based silicone, particularly suitable for damage-free bonding of mirrors of all types and sizes.

- One-component, moisture-hardening.
- Excellent adhesion.
- Not corrosive.
- Fast polymerization.
- Low modulus, high elasticity.
- 100% silicone, solvent free.
- Absence of odor.

APPLICATIONS

Mirrored walls in shops, restaurants, gyms. Bonding of mirrors on plaster, concrete, wood, mirrors on doors or ceramic coverings.



TECHNICAL DATA

| | |
|-------------------------|---------------------------------|
| Base | Silicone Polymer |
| Polymerization system | Acetic |
| Density | 1,02±0.03 g/ml (TS 781 ISO 758) |
| Hardness | 15 ±(3 After 28)Days |
| Tack-free time | 11-12 min. (23°C and 50% R.H) |
| Cure rate | Min. 2 mm/ Day (23°C e 50% R.H) |
| Tensile strength | 1.5 N/mm2 - (ASTM D 412) |
| Elongation at break | ≥500 %- (ASTM D 412) |
| Sagging | 0 mm - (ISO 7390) |
| Application temperature | +5°C to +40°C |
| Temperature resistance | -40°C to +150°C |

TECHNICAL DATA

| | |
|-------------------------|---------------------------------|
| Base | Silicone Polymer (Oxime) |
| Polymerization system | Neutral |
| Density | 1,02±0.03 g/ml (TS 781 ISO 758) |
| Hardness | 20Shore A |
| Tensile strength | 1,5 N/mm2 (ASTM D412) |
| Tack-free time | 12-13 min. (23°C and 50% R.H) |
| Cure rate | Min. 2.5 mm/ Day (23°C 50% R.H) |
| Elongation at break | > 200% |
| Sagging | 2 mm |
| Application temperature | +5°C to +40°C |
| Temperature resistance | -50°C to +150°C |

| Ral | Content | |
|-------|---------|--------|
| White | 280 ml | 25 Pcs |
| Gray | 280 ml | 25 Pcs |
| Black | 280 ml | 25 Pcs |

| Ral | Content | |
|-------|---------|--------|
| Clear | 280 ml | 25 Pcs |

SILICONES

FIRE STOP SILICONE

PROPERTIES

Selsil Fire Stop Silicone is one part neutral curing, gunnable, specially formulated silicone sealant for being barrier against fire. It creates a barrier against fire up to 4 hours.

- Easy application
- Long life reliability and low maintenance
- Superior adhesion to wide range of building materials including concrete and brickwork
- Flexibility with storage time and stock usage
- Can be applied in vertical and overhead joints
- Unaffected by high or low temperatures
- UV Resistant
- Low odor

APPLICATIONS

Selsil Fire Stop Silicone was specifically developed for fire resistant sealing of connection and expansion joints in construction, is fire resistant in case of fire. Selsil Fire Stop Silicone is a high performance neutral cure silicone sealant designed to give superior adhesion and durability in a wide range of glazing, weather sealing and trade applications. Selsil Fire Stop Silicone will bond to form a strong weatherproof seal on most common building materials such as: glass, ceramic, steel, aluminum, brick, concrete, most plastics, etc.



TECHNICAL DATA

| | |
|-------------------------|--------------------------------------|
| Base | Silicone Polymer |
| Polymerization system | Neutral |
| Density | 1,41 ± 0.03 g/ml (TS 781 ISO 758) |
| Hardness | 20 Shore A |
| Tack-free time | Aprox 8 min. (23°C and 50% R.H) |
| Cure rate | 2 mm/ Day (23°C e 50% R.H) |
| Tensile strength | 1,2 N/mm ² - (ASTM D 412) |
| Elongation at break | >200% - (ASTM D 412) |
| Sagging | 0 mm |
| Application temperature | +5°C to +40°C |
| Temperature resistance | -50°C to +150°C |

| Ral | Content | |
|-------|---------|--------|
| White | 280 ml | 25 Pcs |

AUTO-SEL GASKET MAKER

PROPERTIES

Selsil RTV Auto Sealant is on oxime-based, fast curing, durable, flexible and low modules, neutral gasket sealant designed to give superior adhesion and durability in very high temperatures.

APPLICATIONS

It can be used as gasket sealant for automobiles, differential cover, motor cover, carburetor cover and pumps; for sealing in heating systems and thermostat. It is suitable for continuous operation in the temperature range between -50°C and up to +300°C.



TECHNICAL DATA

| | |
|-------------------------|--|
| Base | Silicone Polymer |
| Polymerization system | Acetic |
| Density | 1.14 ± 0.03 g/ml - (TS 781 ISO 758) |
| Hardness | 12-13 (After 28)Days |
| Tensile strength | ≥ 1,5 N/mm ² (23°C and 50% R.H) (ASTM D412) |
| Tack-free time | 7-13 min. (23°C and 50% R.H) |
| Cure rate | Min. 3 mm/ Day (23°C e 50% R.H) |
| Elongation at break | ≥200% |
| Sagging | 0 mm |
| Application temperature | +5°C to +40°C |
| Temperature resistance | -50°C to +250°C |

| Ral | Content | |
|-------|---------|--------|
| Gray | 85 gr | 48 Pcs |
| Black | 85 gr | 48 Pcs |
| Red | 85 gr | 48 Pcs |

ACRYLICS

ACRYLIC SEALANT

PROPERTIES

Selsil Acrylic Sealant is a one-component, universal, acrylic sealant, suitable for filling cracks and joints both indoors and outdoors. Ideal for static joints with an excellent ratio of plasticity and elasticity.

- Over paintable.
- Can be used on all porous surfaces (brick, concrete, wood, etc.)
- Very easy to apply and clean.
- Waterproof after hardening.
- Odorless.

APPLICATIONS

- Sealing of low and medium expansion joints on various types of building materials (wood, concrete, bricks, etc).
- Filling of cracks and crevices in walls and ceilings.
- Sealing of joints between windows, walls, doors, etc.



TECHNICAL DATA

| | |
|-------------------------|---|
| Base | Acrylic polymer |
| Appearance | Thixotropic Paste |
| pH | 7-9 |
| Density | 1.62 ± 0.03 g/ml - (TS 781 ISO 758) |
| Tack-free time | 15-60 min (23°C and 50% R.H) (ASTM C 679) |
| Maximum elongation | ≥ 100 % (ASTM D 412) |
| Application temperature | +5 °C to +35°C |
| Temperature resistance | -10 °C to +80 °C |

| Ral | Content | |
|-------|---------|--------|
| White | 500 gr | 25 Pcs |
| | 600 ml | 20 Pcs |
| Gray | 500 gr | 25 Pcs |
| Black | 500 gr | 25 Pcs |

SILICONIZED ACRYLIC SEALANT

PROPERTIES

Selsil Siliconized Acrylic Sealant is used for PVC, aluminium and wooden panel installation, joints between door /window frames and the wall, joints at washbasin, bathtub, closets, tiles and ceramic, cracks in walls, wood, plaster, aluminium, brick and concrete.

- Ease of application.
- Form permanently water repellent layer after curing.
- Resistant to weather conditions.
- Remains flexible for a long time after curing.
- Paintable.

APPLICATIONS

- Contact area must be dry, clean, free from dust, oil and grease.
- Ensure neat sealant edges mask the areas adjacent to joints with masking tape.
- Cut the tip of the cartridge with angle in accordance with size of the surface to be applied on.
- Place the cartridge in the gun and inject the joint with the sealant.
- The applied sealant should be smoothed immediately with a wet spatula, tool or finger. Remove masking tape right after smoothing.



TECHNICAL DATA

| | |
|-------------------------|---|
| Base | Acrylic polymer |
| Consistency | Soft paste |
| pH | 7-9 |
| Density | 1.63 ± 0.03 g/ml - (TS 781 ISO 758) |
| Tack-free time | 15 - 60 min (23°C and 50% R.H) (ASTM C 679) |
| Elongation at Break | ≥ 100 % (ASTM D 412) |
| Application temperature | +5 °C to +35°C |
| Temperature resistance | -10 °C to +80 °C |

| Ral | Content | |
|-------|---------|--------|
| White | 450 gr | 25 Pcs |

ACRYLICS

EXTERIOR SILICONIZED ACRYLIC

PROPERTIES

Selsil Water Resistant Acrylic Sealant is a water based general-purpose, flexible sealant which is used for jointing and embedding in building construction. It is easy to apply and compatible with most materials used in construction. It is outdoor rated.

- Form permanently water repellent layer after curing.
- Resistant to weather conditions.
- Remains flexible for a long time after curing.
- Paintable.

APPLICATIONS

- Contact area must be dry, clean, free from dust, oil and grease.
- Ensure neat sealant edges mask the areas adjacent to joints with masking tape.
- Cut the tip of the cartridge with angle in accordance with size of the surface to be applied on.
- Place the cartridge in the gun and inject the joint with the sealant
- The applied sealant should be smoothed immediately with a wet spatula, tool or finger.
- Remove masking tape right after smoothing.



TECHNICAL DATA

| | |
|-------------------------|--|
| Base | Acrylic polymer |
| Appearance | Thixotropic Paste |
| pH | 7-9 |
| Density | 1,52 ± 0,03 gr/cm3 (ASTM D 792) |
| Tack-free time | 15 ± 60 min (23°C and 50% R.H.),(ASTM C 679) |
| Elongation at Break | ≥200% (ASTM D412) |
| Temperature resistance | -10°C to +80°C |
| Application temperature | +5°C to +35°C |

| Ral | Content | |
|-----|------------|--------------------------------|
| | White | 485 gr 25 Pcs 400 ml 25 Pcs |
| | Gray | 485 gr 25 Pcs |
| | Ant. Gray | 485 gr 25 Pcs |
| | Brown | 485 gr 25 Pcs |
| | Golden Oak | 485 gr 25 Pcs |
| | Mink | 485 gr 25 Pcs |

SILICONE SEALANT

PROPERTIES

Selsil Silicone-Isolated Acrylic Sealant is used on PVC, aluminum, and wood panel installations, joints between door/window frames and walls, sinks, toilets, tile and ceramic joints, and roofs on walls, wood, plaster, aluminum, brick, and concrete.

- Easy to apply
- Forms a permanent water-repellent layer after curing.
- Remains flexible for a long time after curing
- Paintable

APPLICATIONS

- Joints between building elements,
- Installation of wood, PVC, iron, and aluminum joinery,
- Joining of all types of joinery, plaster, and other building materials,
- Joining of aluminum and aluminum roof and facade panels and all types of building materials,
- Also used before painting to prevent cracks.



TECHNICAL DATA

| | |
|-------------------------|---|
| Base | Acrylic polymer |
| Appearance | Thixotropic Paste |
| pH | 7-9 |
| Density | 1.63 ± 0.03 g/ml - (TS 781 ISO 758) |
| Tack-free time | 15±60 dk (23°C ve 50% R.H) (ASTM C 679) |
| Elongation at Break | ≥100% (ASTM D 412) |
| Temperature resistance | -10°C ile +80°C |
| Application temperature | +5°C ile +35°C |

| Ral | Content | |
|-----|------------|---|
| | White | 500 gr 25 Pcs 400 ml 25 Pcs 600 ml 20 Pcs |
| | Black | 500 gr 25 Pcs |
| | Bronze | 500 gr 25 Pcs |
| | Beige | 500 gr 25 Pcs |
| | Dark Oak | 500 gr 25 Pcs |
| | Light Oak | 500 gr 25 Pcs |
| | Champagne | 500 gr 25 Pcs |
| | Gray | 500 gr 25 Pcs |
| | Ant Gray | 500 gr 25 Pcs |
| | Brown | 500 gr 25 Pcs |
| | Golden Oak | 500 gr 25 Pcs |

ACRYLICS

ACRYLIC SKIRTING ADHESIVE

PROPERTIES

Selsil Acrylic Skirting Adhesive is one part acrylic adhesive. Selsil Acrylic Skirting Adhesive is used for fixing skirting boards in both wood and UPVC, fixing thresholds, panels, ceramic tiles and ornamental framework on to various substrates such as masonry, concrete, plaster board and wood. And it is also suitable for the adhesion of polystyrene foam and tiles. Very easy application. Form permanently water repellent layer after curing. Paintable.

APPLICATIONS

- Contact area must be dry, clean, free from dust, oil and grease.
- Ensure neat sealant edges mask the areas adjacent to joints with Masking tape.
- Cut the tip of the cartridge with angle in accordance with size of the surface to be applied on.
- Place the cartridge in the gun and inject the joint with the sealant.



FIRE STOP ACRYLIC

PROPERTIES

Selsil Fire resistant acrylic sealant is one component, acrylic emulsion based and specially formulated for being barrier against fire. Suitable for below applications; precast panel joints, control joints in masonry blockwork and sealing around metal ducting/pipework etc.

- Water based, contains no asbestos or fibres.
- Easy application.
- Short surface curing.
- Paintable.
- Good adhesion to concrete and masonry substrates.
- Flexible.

APPLICATIONS

- Contact area must be dry, clean, free from dust, oil and grease.
- Ensure neat sealant edges mask the areas adjacent to joints with masking tape.
- Cut the tip of the cartridge with angle in accordance with size of the surface to be applied on.
- Place the cartridge in the gun and inject the joint with the sealant.
- The applied sealant should be smoothed immediately with a wet spatula, tool or finger.
- Remove masking tape right after smoothing.



TECHNICAL DATA

| | |
|-------------------------|-------------------------|
| Base | Acrylic polymer |
| Appearance | Thixotropic Paste |
| Color | White |
| Cure rate | 2 mm/day (25°C; 50% RH) |
| Application Temperature | 5°C to 40°C |
| Temperature resistance | -10°C to +80°C |
| Tack free time | 30-60 min. |
| Elongation at Break | >150 % |
| Tensile Strength | >0.25 N/mm |

TECHNICAL DATA

| | |
|-------------------------|--|
| Base | Acrylic polymer |
| Appearance | Thixotropic Paste |
| pH | 7-9 |
| Density | 1,56±0,03 g/cm ³ (TS 781 ISO 758) |
| Tack-free time | 15± 60 min (23°C and 50% R.H) (ASTM C 679) |
| Elongation at Break | ≥110% (ASTM D412) |
| Temperature resistance | -10 °C to +80 °C |
| Application temperature | +5 °C to +35 °C |

Ral Volume

White 500 gr 25 Pcs

Ral Volume

White 310 ml 25 Pcs

HYBRIDS

X1

PROPERTIES

Selsil X1 General Purpose Assembly Adhesive is a high-quality hybrid polymer-based mastic adhesive.

- It offers high filling and bonding capacity and long life.
- It contains no solvents, silicones, or isocyanates.
- It has low VOC emissions.
- It is suitable for use on wet surfaces. However, it is not suitable for continuous underwater use.
- It has excellent UV resistance.
- It can be painted.
- It will not crack or shrink.
- It provides excellent primer-free adhesion. (A preliminary test is recommended, however).

APPLICATIONS

Selsil Hybrid Classic is suitable for the assembly and bonding of metal, aluminum, glass, plastic, wood, and concrete. It can be used as an elastic adhesive and sealant for many applications in the construction industry, both indoors and outdoors:

- Insulating window and door elements, Joints of wood and metal structures,
- Assembling and insulating exterior facade elements.



TECHNICAL DATA

| | |
|------------------------------|---------------------------|
| Base | Silane Terminated Polymer |
| Curing Mechanism | Moisture |
| Density | 1.56 ± 0.03 gr/ml |
| Hardness | 55±5 Shore A |
| Appearance | Paste, White |
| Tack free time | ~15 dk. (23°C, 50% RH) |
| Cure rate | ~2 mm/24 hour |
| Sagging (ISO 7390) | 0mm |
| Elongation at Break (ISO 37) | >=250 |
| Loss of Volume | <-%3 (23°C, 50% R.H) |
| Tensile Strength (ISO 37) | 1,5-2,0 N/mm2 |
| Temperature resistance | -40°C e +90°C |
| Application temperature | +5°C e +35°C |

| Ral | Volume | Box |
|-------|--------|--------|
| White | 290 ml | 25 Pcs |
| Gray | 290 ml | 25 Pcs |
| Black | 290 ml | 25 Pcs |

MIRROR ADHESIVE

Selsil Mirror Adhesive is a solvent-free, hybrid-based adhesive suitable for indoor and outdoor use, does not damage the glazed surface of mirrors, and provides excellent adhesion without leaving stains even on damp surfaces.

PROPERTIES

- Easy to apply.
- Does not tarnish the mirror and is applied without damaging the line.
- Solvent-free.
- Provides excellent adhesion.
- UV resistant.
- Can be easily applied even on damp surfaces.

APPLICATIONS

- The application surface must be clean, dry, oil-free, and dust-free.
- Cut the cartridge tip at an angle to the size required by the application surface.
- Place the cartridge into the gun.
- If necessary, smooth the surface and polish with water. After polishing, remove the tape.



TECHNICAL DATA

| | |
|----------------------|--------------------------|
| Ürün Tipi | Silan Termine Polimer |
| Kürleşme Mekanizması | Nem and Kürleşme |
| Yoğunluk | 1.48 ± 0.03 g/ml |
| Appearance/Renk | Macun/White |
| Yüzey Kuruması | 3-5 dk. (23°C ve 50% RH) |
| Akma | 2 mm/24 hour |
| Sertlik | 55 ± 5 Shore A |
| Kopma Anında Uzama | >200% |
| Kopma Dayanımı | >1,7 N/mm² |
| Isıl Dayanım | -10°C ile +80°C |
| Uygulama Sıcaklığı | +5°C ile +40°C |

| Ral | Volume | Box |
|-------|--------|--------|
| White | 280ml | 25 Pcs |

HYBRIDS

ULTRA CLEAR CRYSTAL TRANSPARENT ADHESIVE

PROPERTIES

Selsil Ultra Clear / Shore A35 Crystalline Hybrid Sealant is a perfectly transparent, elastic, highly thixotropic adhesive. Ideal for both vertical and horizontal applications. Paintable. Does not shrink.

- Does not contain solvents, silicones and isocyanates.
- Strong adhesion on many surfaces.
- Does not foam with moisture.
- Does not require primer.
- Compliant with specification requirements for VOC content.

APPLICATIONS

- Excellent adhesive power even without primer on all of the most common materials such as aluminum, zinc, galvanized steel, stainless steel, copper, stone, concrete, bricks, etc.
- Perfect for application as transparent and elastic bonding in the construction field.
- Bonding and sealing of glass and other transparent materials in indoor applications.



ULTRA TACK STRONG ADHESIVE

PROPERTIES

Selsil Shore A55 Hybrid Adhesive is a one-component, high quality and professional hybrid polymer-based adhesive with high adhesion and very high initial tack. Suitable for bonding heavy construction materials without the use of clamps and/or fixing tapes. Does not contain solvents or isocyanates.

APPLICATIONS

- Developed for adhesion to the widest range of building materials: stone, concrete, mirrors, glass, plasterboard, PU, PVC, polyester, plastic, ceramic, iron, zinc, wood.
- Wall covering elements and ceiling panels, panels for acoustic insulation and thermal insulation.
- Frames and structures in building construction, wooden and plastic laths, ornaments and frames, door steps, window sills, skirting boards and cover plates.



TECHNICAL DATA

| | |
|-------------------------|----------------------------|
| Chemical Base | Silane Terminated Polymer |
| Curing Mechanism | Moisture |
| Density | 1.02 ± 0.03 gr/ml |
| Appearance | Paste, Transparent |
| Tack-free time | 35 min (23°C and %50 R.H.) |
| Cure rate | 25.5 mm/ 24 hr |
| Hardness | 35±5 Shore A |
| Elongation at break | ≥ 300% |
| Loss of Volume | < -%3 (23°C and %50 R.H.) |
| Tensile strength | 1,9N/mm ² |
| Temperature resistance | -40°C e +90°C |
| Application temperature | +5°C e +40°C |

| | Ral | Volume | |
|-------------------------------------|-------------------|--------|--------|
| <input checked="" type="checkbox"/> | Glass Transparent | 290 ml | 25 Pcs |
| | | 50 ml | 12 Pcs |

TECHNICAL DATA

| | |
|---------------------------------|----------------------------|
| Chemical Base | Silane Terminated Polymer |
| Curing Mechanism | Moisture |
| Density | 1.56 ± 0.03 g/ml |
| Appearance | Paste |
| Tack-free time | 5-10 min (23°C and 50% RH) |
| Sagging | 0 mm |
| Shore A | 50 ± 5 |
| Elongation at break % (ISO 37) | > %300 |
| Volume loss | < -%3 (23°C and %50 RH) |
| Tensile strength (ISO 37) | >2 |
| Temperature resistance (ISO 37) | -40°C to +90°C |
| Application temperature | +5°C to +40°C |

| | Ral | Volume | |
|--------------------------|-------|--------|--------|
| <input type="checkbox"/> | White | 290 ml | 12 Pcs |
| | | 50 ml | 12 Pcs |
| <input type="checkbox"/> | Black | 290 ml | 25 Pcs |

POLYURETHANES

WATER STOP LIQUID MEMBRANE

PROPERTIES

Selsil Water Stop Liquid Membrane, a one-component, hybrid polymer-based, low-viscosity waterproofing product. Free from solvents, isocyanates, and bitumen. Upon contact with air, it cures to form an elastic and waterproof layer. Easily applicable on both horizontal and vertical surfaces.

APPLICATIONS

Before application, necessary safety measures must be taken and personal protective equipment should be worn. The surface must be clean, dry, or slightly damp, and all oil, dust, dirt, and loose particles should be removed. The product can be applied using a brush, roller, or airless spray. For best performance, a double-coat application is recommended, ensuring that the first coat is completely dry before applying the second one. After application, the product should not be exposed to water for at least twenty-four hours. Tools used during application can be cleaned with alcohol or acetone before the product cures; once cured, they can only be cleaned by scraping. The product should be stored in a cool and dry environment at temperatures between +5 °C and +25 °C, where it retains a shelf life of twelve months.



TECHNICAL DATA

| | |
|-------------------------|-------------------------------|
| Product Type | Modified Silane Polymer |
| Curing Mechanism | Atmospheric Moisture |
| Density | 1.43 ± 0.03 g/cm ³ |
| Appearance / Color | Grey |
| Tack-Free Time | 30 ± 5 min (25°C and 50% RH) |
| Hardness | 38 ± 5 Shore A |
| Elongation at Break | 250% ± 50 |
| Tensile Strength | 1.5 - 2 MPa |
| Temperature Resistance | -30°C to +80°C |
| Application Temperature | +5°C to +35°C |

| Ral | Volume | |
|------|--------------|--------|
| Gray | 14kg (2x7kg) | 39 Pcs |

POLYURETHANES

PU25

PROPERTIES

Selsil SPU-40 Polyurethane Sealant for Metal/Construction is a medium modulus one-component polyurethane sealant that cures when exposed to atmospheric humidity. It has excellent adhesion to all of the most common building materials such as concrete, brick, ceramic, glass, wood, galvanized and painted sheet and various plastics. Paintable. Does not vary in volume.

APPLICATIONS

- Exceptional thixotropy.
- Expansion joints in floors, indoor and outdoor applications for pedestrian and busy areas, prefabricated concrete panels.
- Sealing against water, air, gas and dust.



TECHNICAL DATA

| | |
|-------------------------|----------------------------------|
| Chemical Base | Polyurethane |
| Appearance | Thixotropic Paste |
| Curing Mechanism | Moisture |
| Density | 1,15 ± 0,03 g/ml |
| Tack-free time | 60-90 min. (23°C and 50% R.H) |
| Cute rate | Min. 2 mm/ Day (23°Ce 50% R.H) |
| Temperature resistance | -30 °C to +80 °C |
| Application temperature | +5°C to +35°C |
| Hardness | 20 ± 5 After 28 Days (ASTM C661) |
| Paintable | Yes |
| Elastic recovery | ≥70% (ISO 7389) |
| E100 Module (23°C) | 0,4N/mm ² (ISO8339) |
| Elongation at break | 500% (ASTM D412) |
| Tensile strength | 1,3N/mm ² (ASTM D412) |

| Ral | Volume | |
|-------|--------|--------|
| White | 280ml | 25 Pcs |
| Gray | 280ml | 25 Pcs |
| Black | 280ml | 25 Pcs |
| White | 600ml | 20 Pcs |
| Gray | 600ml | 20 Pcs |
| Black | 600ml | 20 Pcs |

PU40

PROPERTIES

Selsil SPU-40 Polyurethane Sealant for Metal/Construction is a medium modulus one-component polyurethane sealant that cures when exposed to atmospheric humidity. It has excellent adhesion to all of the most common building materials such as concrete, brick, ceramic, glass, wood, galvanized and painted sheet and various plastics. Paintable. Does not vary in volume.

APPLICATIONS

- Exceptional thixotropy.
- Expansion joints in floors, indoor and outdoor applications for pedestrian and busy areas, prefabricated concrete panels.
- Sealing against water, air, gas and dust.



TECHNICAL DATA

| | |
|-------------------------|----------------------------------|
| Chemical Base | Poliurethane |
| Curing Mechanism | Moisture |
| Density | 1.15 ± 0.03 g/ml |
| Tack-free time | 60-90 min. (23°C and 50% RH) |
| Cute rate | Min. 2 mm/Day (23°C and 50% RH) |
| Temperature resistance | -30 °C to + 80 ° C |
| Application temperature | + 5 °C to + 35 ° C |
| Hardness | 40±5 Shore A |
| Paintable | Yes |
| Elastic recovery | ≥ 70% (ISO 7389) |
| E100 Module (23°C) | 0.40 N/mm ² (ISO8339) |
| Elongation at break | 500% (ASTM D412) |
| Tensile strength | 1.3 N/mm ² (ASTMD412) |

| Ral | Volume | |
|--------|--------|--------|
| White | 280 ml | 25 Pcs |
| Gray | 280 ml | 25 Pcs |
| Black | 280 ml | 25 Pcs |
| Tile | 280 ml | 25 Pcs |
| A.Gray | 280 ml | 20 Pcs |
| White | 280 ml | 20 Pcs |
| Gray | 280 ml | 20 Pcs |
| Black | 280 ml | 20 Pcs |
| A.Gray | 280 ml | 20 Pcs |

POLYURETHANES

PU50

PROPERTIES

Selsil SPU-50 Polyurethane Sealant for Metal/Construction is a medium modulus one-component polyurethane sealant that cures when exposed to atmospheric humidity. It has excellent adhesion to all of the most common building materials such as concrete, brick, ceramic, glass, wood, galvanized and painted sheet and various plastics. Paintable. Does not vary in volume.

APPLICATIONS

- Exceptional thixotropy.
- Expansion joints in floors, indoor and outdoor applications for pedestrian and busy areas, prefabricated concrete panels.
- Sealing against water, air, gas and dust.



TECHNICAL DATA

| | |
|-------------------------|--|
| Chemical base | Polyurethane |
| Curing Mechanism | Moisture |
| Density | 1,15 ± 0,03 g/ml |
| Tack-free time | 60-90 min. (23°C and 50% R.H) |
| Cute rate | 2 mm/24hour |
| Temperature resistance | -30°C to +80°C |
| Application temperature | +5°C to +35 °C |
| Hardness | 50 ± Shore A |
| Paintable | Yes |
| Elastic recovery | ≥ 70% (ISO 7389) |
| E100 Module (23°C) | 1 N/mm ² (ISO8339) |
| Elongation at break | 500 % (ASTM D412) |
| Tensile strength | 1,5 ± 0,2 N/m ² (ASTM D412) |

| Ral | Volume | Box | Ral | Volume | Box |
|-------|--------|--------|---------|--------|--------|
| White | 280ml | 25 Pcs | Gray | 600 ml | 20 Pcs |
| Gray | 280ml | 25 Pcs | Black | 600 ml | 20 Pcs |
| Black | 280ml | 25 Pcs | Kirmizi | 600 ml | 20 Pcs |
| White | 600ml | 20 Pcs | | | |

PU60

PROPERTIES

Selsil SPU-60 Polyurethane Sealant for Metal/Construction is a medium modulus one-component polyurethane sealant that cures when exposed to atmospheric humidity. It has excellent adhesion to all of the most common building materials such as concrete, brick, ceramic, glass, wood, galvanized and painted sheet and various plastics. Paintable. Does not vary in volume.

APPLICATIONS

- Exceptional thixotropy.
- Expansion joints in floors, indoor and outdoor applications for pedestrian and busy areas, prefabricated concrete panels.
- Sealing against water, air, gas and dust.



TECHNICAL DATA

| | |
|-------------------------|------------------------------|
| Chemical base | Polyurethane |
| Curing Mechanism | Moisture |
| Density | 1.15 ± 0.03 g/ml |
| Tack-free time | 60-90 min. (23°C and 50% RH) |
| Cute rate | 2 mm/24hour |
| Sagging | 2 mm (EN ISO 7390) |
| Temperature resistance | -30 °C to + 80 °C |
| Application temperature | + 5 °C to + 35 °C |
| Hardness | 60±5 Shore A |
| Paintable | Yes |
| Elastic recovery | ≥ 70% (ISO 7389) |
| E100 Module (23°C) | 1 N/mm ² |
| Elongation at break | 450% (ASTM D412) |
| Tensile strength | 2 N/mm ² |

| Ral | Volume | Box | Ral | Volume | Box |
|-------|--------|--------|-------|--------|--------|
| White | 280ml | 25 Pcs | White | 600 ml | 20 Pcs |
| Gray | 280ml | 25 Pcs | Gray | 600 ml | 20 Pcs |
| Black | 280ml | 25 Pcs | Black | 600 ml | 20 Pcs |

MARINE

Selsil[®]

MARINE DECK SEALANT

PROPERTIES

Selsil Marine Deck Sealant is suitable for sealing teak decks in boats, yachts and commercial ships and provides elasticity. The application surface must be solid, clean, dry and free of dust, oil and grease. The teak has to be pretreated with Selsil Primer and after drying Selsil Marine Deck Sealant can be applied with a mastic gun. The product has to be tooled within 25 minutes. Do not apply to frozen or wet surfaces. Avoid contact with alcohol and solvents during curing

APPLICATIONS

- Solvent and isocyanate free
- No release of volatile organic components (VOC's)
- No bubble formation
- High adhesion property
- UV and weather resistance
- Sandable after curing
- Resistant to salt and fresh water



TECHNICAL DATA

| | |
|-------------------------|-----------------------------------|
| Chemical base | Hybrid-MS polymer |
| Curing Mechanism | Moisture |
| Density | 1,40±0,03 g/ml |
| Tack-free time | 25-5min.(23°C and 50% R.H) |
| Cute rate | Min. 2,5 mm/ Day (23°C e 50% R.H) |
| Temperature resistance | -40°C to +90°C |
| Application temperature | +5°C to +35°C |
| Hardness | 50±5 Shore A |
| Elongation at break | % 300 (ASTM D412) |
| Tensile strength | 3 N/mm ² (ASTM D412) |

| Ral | Volume | |
|-------|--------|--------|
| Black | 280 ml | 25 Pcs |
| | 600 ml | 20 Pcs |

MARINE BEDDING ADHESIVE

PROPERTIES

Selsil Marine Deck and Bedding Adhesive is for bedding in keels, molding, and deck hardware. Selsil Marine Deck and Bedding Adhesive is for bedding and bonding watertight plywood subdeck on a steel, aluminum, polyester or wooden subdeck. The application surface must be solid, clean, dry and free of dust, oil and grease. Selsil Marine Deck and Bedding Adhesive can be applied with a mastic gun. The product has to be tooled within 25 minutes. For an optimum use of the high deformability of Selsil Marine Deck and Bedding Adhesive minimum thickness of 2 mm for the adhesive layer is recommended. Do not apply to frozen or wet surfaces. Avoid contact with alcohol and solvents during curing. Store the product in a cool and dry place. Avoid contact with eyes and skin, use gloves.

APPLICATIONS

- Solvent and isocyanate free
- No release of volatile organic components (VOC's)
- No bubble formation
- High adhesion property
- UV and weather resistance
- Resistant to salt and fresh water



TECHNICAL DATA

| | |
|-------------------------|-----------------------------------|
| Chemical base | Hybrid-MS polymer |
| Curing Mechanism | Moisture |
| Density | 1,32 ± 0,03 g/ml |
| Tack-free time | 25-5min.(23°C and 50% R.H) |
| Cute rate | Min. 2,5 mm/ Day (23°C e 50% R.H) |
| Temperature resistance | -40°C to +90°C |
| Application temperature | +5°C to +35°C |
| Hardness | 35 ± 5 Shore A |
| Elongation at break | % 250 (ASTM D412) |
| Tensile strength | 2.2 N/mm ² (ASTM D412) |

| Ral | Volume | |
|-------|--------|--------|
| Brown | 280 ml | 25 Pcs |
| | 600 ml | 20 Pcs |

PU MARINE GRADE ADHESIVE

PROPERTIES

Selsil PU Marine Adhesive, is a one component, polyurethane based wood adhesive, which cures with moisture of air and has excellent resistance abilities to impact of water. It can be used for installing of MDF, slab surfaces, formica and door frames, construction of wood, made ships and yachts and furniture industry.

APPLICATIONS

All surfaces to be bonded must be clean and free of dust and grease and sended. Moisturizing the materials will help the hardening process. Surfaces to be bonded as humidity and temperature requirement 40-45 min. Should be kept under press. The surfaces that shouldnt be apposed must be cleaned with acetone before drying.



TEAK CLEANER SPRAY

PROPERTIES

Selsil Teak Cleaner Spray is developed for easily removing grease, strain, and other dirt from teak decks. Shake vigorously before use. Spray to the surface from 10-15 cm to completely cover the surface. Wait for 15-20 minutes and wash the surface with water. Repeat it if it is necessary.

APPLICATIONS

- Excellent cleaning
- Easy application
- Aromatic smell



TECHNICAL DATA

| | |
|------------------------|--------------------------------|
| Chemical base | Polyurethane |
| Curing Mechanism | Moisture |
| Density | 1.14 g/ml |
| Tack-free time | 15 ± 3 min. (23°C and 50% R.H) |
| Cure rate | -30°C to +80°C |
| Temperature Resistance | +5°C to +35°C |
| Viscosity | 7700 ± 1300 cPS |

| Ral | Volume |  |
|---|--------|---|
|  Clear | 500 gr | 12 Pcs |
|  Honey | 500 gr | 12 Pcs |
| | 1 kg | 12 Pcs |
| | 5 kg | 1 Pcs |

| Ral | Volume |  |
|---|--------|---|
|  - | 500 ml | 12 Pcs |

POLYURETHANE FOAMS

Selsil[®]

FILLING AND ADHESIVE

PU FOAM (MANUAL) 750G GROSS

PROPERTIES

Selsil Polyurethane Foam (Manual) is a one-component, self-hardening and self-expanding polyurethane foam. Ideal for filling and insulation operations. Does not contain propellant gases harmful to the ozone layer.

APPLICATIONS

- Filling and sealing of slits, particularly large joints and cavities.
- Fixing and insulation of windows and doors.
- Filling holes in walls.
- Insulation of electrical outlets and water pipes.



PU FOAM (GUN GRADE) 750 G GROSS

PROPERTIES

Selsil Polyurethane Foam (Gun) is a one-component, self-hardening and self-expanding polyurethane foam. Ideal for filling and insulation operations. Does not contain propellant gases harmful to the ozone layer.

APPLICATIONS

- Filling and sealing of particularly large cracks, joints and cavities.
- Fixing and insulation of doors and windows.
- Filling of holes in walls.
- Insulation of electrical outlets and water pipes.



TECHNICAL DATA

| | |
|------------------------------------|-------------------------------------|
| Base | Polyurethane Prepolymer |
| Polymerization system | Moisture hardening |
| Specific gravity | 23±3 kg/m ³ (ASTM D1622) |
| Tack-free time (L 1cm) | 6 min (ASTM C1620) |
| Cutting time (L 1cm) | 15-30 min (ASTM C1620) |
| Fire resistance after crosslinking | B3 (DIN 4102-1) |
| Compression strength | 32,6 kPa (DIN 53421) |
| Tensile strength | 52,2 kPa (SO1926-79) |
| Color | Light yellow |
| Yield | 30-45 L (ASTM C1536) |
| Dimensional stability | -1,33 % (ISO 2796/86) |
| Can temperature | min. 20°C max. +25°C |
| Temperature resistance | -30°C to +80°C |
| Application temperature | 5°C to +35°C |

| Ral | Volume | |
|-----|---------------|--------|
| - | 750 ml/600 gr | 16 Pcs |
| - | 750 ml/640 gr | 16 Pcs |
| - | 750 ml/750 gr | 16 Pcs |

TECHNICAL DATA

| | |
|------------------------------------|-------------------------------------|
| Base | Polyurethane Prepolymer |
| Polymerization system | Moisture hardening |
| Specific gravity | 20±3 kg/m ³ (ASTM D1622) |
| Tack-free time (L 1cm) | 5-6 min (ASTM C1620) |
| Cutting time (L 1cm) | 15-30 min (ASTM C1620) |
| Fire resistance after crosslinking | B3 (DIN 4102-1) |
| Compression strength | 25 kPa (DIN 53421) |
| Tensile strength | 35,7 kPa (SO1926-79) |
| Color | Light yellow |
| Yield | 30-45 L (ASTM C1536) |
| Dimensional stability | -0.29 % (ISO 2796/86) |
| Can temperature | min. 20°C max. +25°C |
| Temperature resistance | -30°C to +80°C |
| Application temperature | 5°C to +35°C |

| Ral | Volume | |
|-----|------------------|--------|
| - | 750 ml 750 gr | 16 Pcs |

FILLING AND ADHESIVE

PU FOAM (MANUAL) 845 G

PROPERTIES

Selsil Polyurethane Foam (Manual) is a one-component, self-hardening and self-expanding polyurethane foam. Ideal for filling and insulation operations. Does not contain propellant gases harmful to the ozone layer.

APPLICATIONS

- Filling and sealing of slits, particularly large joints and cavities.
- Fixing and insulation of windows and doors.
- Filling holes in walls.
- Insulation of electrical outlets and water pipes.



PU FOAM (GUN GRADE) 845 G

PROPERTIES

Selsil Polyurethane Foam (Gun) is a one-component, self-hardening and self-expanding polyurethane foam. Ideal for filling and insulation operations. Does not contain propellant gases harmful to the ozone layer.

APPLICATIONS

- Filling and sealing of particularly large cracks, joints and cavities.
- Fixing and insulation of doors and windows.
- Filling of holes in walls.
- Insulation of electrical outlets and water pipes.



TECHNICAL DATA

| | |
|------------------------------------|-------------------------------------|
| Base | Polyurethane Prepolymer |
| Polymerization system | Moisture hardening |
| Specific gravity | 23±3 kg/m ³ (ASTM D1622) |
| Tack-free time (L 1cm) | 6 min (ASTM C1620) |
| Cutting time (L 1cm) | 15-30 min (ASTM C1620) |
| Fire resistance after crosslinking | B3 (DIN 4102-1) |
| Compression strength | 32,6 kPa (DIN 53421) |
| Tensile strength | 52,2 kPa (SO1926-79) |
| Color | Light yellow |
| Yield | 30-45 L (ASTM C1536) |
| Dimensional stability | -1,33 % (ISO 2796/86) |
| Can temperature | min. 20°C max. +25°C |
| Temperature resistance | -30°C to +80°C |
| Application temperature | 5°C to +35°C |

TECHNICAL DATA

| | |
|------------------------------------|-------------------------------------|
| Base | Polyurethane Prepolymer |
| Polymerization system | Moisture hardening |
| Specific gravity | 20±3 kg/m ³ (ASTM D1622) |
| Tack-free time (L 1cm) | 5-6 min (ASTM C1620) |
| Cutting time (L 1cm) | 15-30 min (ASTM C1620) |
| Fire resistance after crosslinking | B3 (DIN 4102-1) |
| Compression strength | 25 kPa (DIN 53421) |
| Tensile strength | 35,7 kPa (SO1926-79) |
| Color | Light yellow |
| Yield | 30-45 L (ASTM C1536) |
| Dimensional stability | -0.29 % (ISO 2796/86) |
| Can temperature | min. 20°C max. +25°C |
| Temperature resistance | -30°C to +80°C |
| Application temperature | 5°C to +35°C |

| | | |
|-----|------------------|--------|
| Ral | Volume | |
| - | 750 ml 845 gr | 16 Pcs |

| | | |
|-----|------------------|--------|
| Ral | Volume | |
| - | 750 ml 845 gr | 16 Pcs |

FILLING AND ADHESIVE

PU ADHESIVE FOAM (MANUAL)

PROPERTIES

Selsil Foam for Pantiles and Tiles, Insulating Panels and Plasterboard (Manual) is a one-component polyurethane adhesive foam that cures rapidly with humidity, with controlled expansion. Provides very strong and fast adhesion on various building materials.

APPLICATIONS

- Ideal for fixing tiles and pantiles, thermal and acoustic insulation panels, plasterboard sheets.
- Recommended for bonding wood and concrete building materials.
- Ideal for applications requiring minimal foam expansion (door and window installation).



TECHNICAL DATA

| | |
|------------------------------------|-------------------------------------|
| Base | Polyurethane Prepolymer |
| Polymerization system | Moisture hardening |
| Specific gravity | 21±3 kg/m ³ (ASTM D1622) |
| Tack-free time (L 1cm) | 6±2 min (ASTM C1620) |
| Cutting time (L 1cm) | 30-40 min (ASTM C1620) |
| Color | Pink |
| Yield | 45-55 L (ASTM C1536) |
| Coverage area | Up to 5-10 m ² |
| Fire resistance after crosslinking | B3,E (DIN 4102-1) (EN 13501-1) |
| Compressive strength | 50,2 kPa (DIN 53421) |
| Temperature resistance | -30°C to +80°C |
| Application temperature | 5°C to +35°C |
| Tensile Strength | 79,3 kPa |

Ral Volume

- 850 gr 12 Pcs

PU ADHESIVE FOAM (GUN)

PROPERTIES

Selsil Foam for Pantiles and Tiles, Insulation and Plasterboard (Gun) is a one-component polyurethane adhesive foam that cures rapidly with humidity, with controlled expansion. Provides very strong and fast adhesion on various building materials.

APPLICATIONS

- Ideal for fixing tiles and pantiles, thermal and acoustic insulation panels, plasterboard sheets.
- Recommended for bonding wood and concrete building materials.
- Ideal for applications requiring minimal foam expansion (door and window installation).



TECHNICAL DATA

| | |
|------------------------------------|-------------------------------------|
| Base | Polyurethane Prepolymer |
| Polymerization system | Moisture hardening |
| Specific gravity | 17±3 kg/m ³ (ASTM D1622) |
| Tack-free time (L 1cm) | 6±2 min (ASTM C1620) |
| Cutting time (L 1cm) | 30 min (ASTM C1620) |
| Crosslinking time | 24 hours |
| Color | Pink |
| Yield | 45-55 L (ASTM C1536) |
| Coverage area | Up to 5-10 m ² |
| Fire resistance after crosslinking | B3,E (DIN 4102-1) (EN 13501-1) |
| Compressive strength | 50,2 kPa (DIN 53421) |
| Temperature resistance | -30°C to +80°C |
| Application temperature | 5°C to +35°C |
| Tensile Strength | 79,3 kPa |

Ral Volume

- 850 gr 12 Pcs

FILLING AND ADHESIVE

FAST CURING ADHESIVE FOAM (GUN)

PROPERTIES

Selsil Fast Adhesive Foam "TOP20" is a one-component polyurethane foam that is cured by action of the moisture present in the air. It can be used for bonding polystyrene sheets (XPS or EPS) used in the thermal insulation of buildings and structural elements such as decorative jambs. It can also be applied to fill and insulate the spaces between the building elements (therefore excellent, given also its low post expansion, for the assembly of windows and doors).

APPLICATIONS

During application, the panel and the gun must be perpendicular, and the distance maintained should allow continuous application. Foam should be applied along the edges of the panel while maintaining a distance of about 2 cm from the edges. The panel should be applied immediately after applying the foam and must be pressed against the wall. After fixing a certain number of panels, they must be aligned with a levelling ruler, and the excess foam should be wiped with a spatula or cutter (or a cloth if still damp).



THERMAL AND ACOUSTIC SPRAY FOAM

PROPERTIES

Selsil Fast Foam for Thermal insulation "ISOLTOP" is a high quality, one-component insulating polyurethane foam. Quickly provides good thermal and acoustic insulation even on large areas. Can be used on uneven surfaces and hard-to-reach places where it is not possible to use traditional insulating materials.

APPLICATIONS

The application surface must be clean, dry, free from dust and oil or grease. The can must be shaken vigorously for about 25/30 times before use. Moisten the application surfaces by spraying water on them (this facilitates perfect cross-linking of the foam). Always keep the can upside down during application. Screw the can on the gun. The amount of foam can be adjusted by pressing the trigger or by acting on the screw adjustment on the back of the gun. For vertical application (walls), spray the foam from a distance of about 30 cm from the surface. For horizontal application (ceiling), spray from a distance of 15-20 cm. The product can (and should) be applied in layers, more layers provide better insulation.



TECHNICAL DATA

| | |
|------------------------------------|-------------------------------------|
| Base | Polyurethane Prepolymer |
| Polymerization system | Moisture hardening |
| Specific gravity | 18±2 kg/m ³ (ASTM D1622) |
| Tack-free time (L 1cm) | 2 min (AST C1622) |
| Cutting time (L 1cm) | 10-15 min (ASTM C1620) |
| Fire resistance after crosslinking | B3 (DIN 4102-1) |
| Compressive strength | 25 kPa (DIN 53421) |
| Tensile strength | 45,11 kPa (SO1926-79) |
| Color | Light yellow |
| Yield | 30-45 L (ASTM C1536) |
| Dimensional stability | <-5% (ISO2796/86) |
| Can temperature | min. 20°C max. +25°C |
| Temperature resistance | -30°C to +80°C |
| Application temperature | 5°C to +35°C |

| | | |
|-----|--------|--------|
| Ral | Volume | |
| - | 850 gr | 12 Pcs |

TECHNICAL DATA

| | |
|------------------------------------|--------------------------|
| Base | Polyurethane Prepolymer |
| Polymerization system | Moisture hardening |
| Specific gravity | 15-20 kg/ M3 (ASTMC1620) |
| Tack-free time (L 1cm) | 5 min (AST C1622) |
| Cutting time (L 1cm) | 60 min (ASTM C1620) |
| Crosslinking time | 24 h |
| Fire resistance after crosslinking | B3 (DIN 4102-1) |
| Thermal conductivity | 0,025-0,03 W/m.K |
| Color | Blue |
| Can temperature | min. 20°C max. +25°C |
| Temperature resistance | -30°C to +80°C |
| Application temperature | 5°C to +35°C |

| | | |
|-----|--------|--------|
| Ral | Volume | |
| - | 930 gr | 12 Pcs |

FILLING AND ADHESIVE

STONE & BRICK ADHESIVE (GUN)

PROPERTIES

Thanks to its "collapsing gel technology", Selsil Adhesive Foam for Blocks And Stone "FORCE PLUS" is the ideal solution for laying adjusted blocks and bricks, stone in general and concrete. The particular formulation means that the foam, instead of swelling, reduces its volume after extrusion, creating a powerful adhesive film that guarantees perfect solidity of the product, avoiding excessive thickness (and hence useless and harmful thermal bridges). It is a one-component polyurethane foam that is cured by action of the moisture present in the air.

APPLICATIONS

The can must be shaken vigorously about 25/30 times before use, then screwed onto the special dispensing gun. The quantity of foam dispensed can be adjusted by pressing the trigger or by acting on the screw adjustment on the back of the gun. It is in gel form, it does not expand once extruded. Moisten the application surfaces by spraying water on them (this facilitates perfect cross-linking of the foam). Keep the can upright during application. Apply the foam on the surfaces (2 lines of adhesive parallel to each other and 5 to 10 cm apart) and press to make them adhere.



TECHNICAL DATA

| | |
|-------------------------|-------------------------|
| Base | Polyurethane Prepolymer |
| Polymerization system | Moisture hardening |
| Tack-free time (L 1cm) | 5-7 min (ASTM C1622) |
| Full curing time | 15-30 min. |
| Shear bond strength | 10-15 N/mm ² |
| Initial grab | 15 min |
| Open time | <2 min |
| Color | Light yellow |
| Temperature resistance | -30°C to +80°C |
| Application temperature | 5°C to +35°C |

| | | |
|-----|--------|--------|
| Ral | Volume | |
| - | 850 gr | 12 Pcs |

LOW EXPANSION FOAM (GUN)

PROPERTIES

Selsil Low Expansion Foam is designed for a wide range of building applications; mounting, sealing, filling and insulating. Low pressure formula prevents the bending of window frames. For fixation of doors, window and door frames, for filling of holes and cracks and to insulate hot and cold water pipes.

APPLICATIONS

Shake the can well approximately 20-25 times before use. Turn the dosage trigger and insert the valve or into the gun. The surface should be free of dirt, dust and grease; and to accelerate the reaction and have the best result the surface and the foam should be wet. Use the can in upside down position. The dried pieces of PU Foam should be removed from the valve or the gun, it can be cleaned by using Selsil Foam Cleaner. Please take into account that the volume of the foam expands.



TECHNICAL DATA

| | |
|------------------------------------|---------------------------|
| Base | Polyurethane Prepolymer |
| Polymerization system | Moisture hardening |
| Specific gravity | 15 ± 3 kg/ M3 (ASTMC1620) |
| Tack-free time (L 1cm) | 10 min (AST C1622) |
| Cutting time (L 1cm) | 15-30 min (ASTM C1620) |
| Fire resistance after crosslinking | 3 (DIN 4102-1) |
| Color | Yellow |
| Can temperature | min. 20°C max. +25°C |
| Temperature resistance | -30°C to +80°C |
| Application temperature | 5°C to +35°C |
| Tensile Strenght | 44,2 kPa |
| Compressive Strenght | 19,9 kPa |
| Dimensional Stability | -1,09 % |

| | | |
|-----|--------|--------|
| Ral | Volume | |
| - | 850 gr | 12 Pcs |

FILLING AND ADHESIVE

B1 FIRE-RESISTANT FOAM (MANUAL)

PROPERTIES

Selsil Fire-Resistant Foam (Manual) is a one-component, self-expanding polyurethane foam containing propellants that are completely harmless to the ozone layer. Ideal where a high resistance to fire is required, guaranteeing a flame retardancy up to 240 minutes (B1).

APPLICATIONS

- All applications where flame retardant properties are required.
- Installation of windows, filling and sealing of empty spaces, joints and cavities.
- Filling of holes in walls.
- Thermal insulation in the construction of roofs, sealing of cables and pipes, bonding of insulating materials.
- Multi-purpose, adhesion and fixing.



TECHNICAL DATA

| | |
|------------------------------------|-------------------------|
| Base | Polyurethane Prepolymer |
| Polymerization system | Moisture hardening |
| Specific gravity | 17±3 kg/m3 (ASTM D1622) |
| Tack-free time (L 1cm) | 6±2 min (ASTM C1620) |
| Cutting time (L 1cm) | 15-30 min (ASTM C1620) |
| Color | Light orange |
| Yield | 45-50L (ASTM C1536) |
| Post expansion | 86% |
| Fire resistance after crosslinking | B1 (DIN 4102) |
| Compressive strength | 41,5 kPa (DIN 53421) |
| Temperature resistance | -30°C to +80°C |
| Application temperature | +5°C to +30°C |
| Can temperature | +20°C to +25°C |
| Dimensional Stability | -0,87 % |
| Tensile Strength | 104,8 kPa |

| | | |
|-----|--------|--------|
| Ral | Volume | |
| ■ - | 900 gr | 12 Pcs |

B1 FIRE-RESISTANT FOAM (GUN)

PROPERTIES

Selsil Fire-Resistant Foam (Gun) is a one-component, self-expanding polyurethane foam containing propellants that are completely harmless to the ozone layer. Provides resistance to fire, guaranteeing a flame retardancy up to 240 minutes (B1)

APPLICATIONS

- All applications where flame retardant properties are required.
- Installation of windows, filling and sealing of empty spaces, joints and cavities.
- Filling of holes in walls.
- Thermal insulation in the construction of roofs, sealing of cables and pipes, bonding of insulating materials.
- Multi-purpose, adhesion and fixing.



TECHNICAL DATA

| | |
|------------------------------------|-------------------------|
| Base | Polyurethane Prepolymer |
| Polymerization system | Moisture hardening |
| Specific gravity | 17±3 kg/m3 (ASTM D1622) |
| Tack-free time (L 1cm) | 6±2 min (ASTM C1620) |
| Cutting time (L 1cm) | 15-30 min (ASTM C1620) |
| Color | Light orange |
| Yield | 45-50L (ASTM C1536) |
| Post expansion | 86% |
| Fire resistance after crosslinking | B1 (DIN 4102) |
| Compressive strength | 41,5 kPa (DIN 53421) |
| Temperature resistance | -30°C to +80°C |
| Application temperature | +5°C to +30°C |
| Can temperature | +20°C to +25°C |
| Dimensional Stability | -0,87 % |
| Tensile Strength | 104,8 kPa |

| | | |
|-----|--------|--------|
| Ral | Volume | |
| ■ - | 900 gr | 12 Pcs |

FILLING AND ADHESIVE

DUAL VALVE FOAM

PROPERTIES

Selsil Dual Valve Foam is a general-purpose, ready-to-use polyurethane foam that can be used for filling and curing. The hand-held valve provides ease of use and allows for gun-like application. Its special formula, which can be applied at 360°C, allows for application from any angle. It is used for fixing doors, windows, and door frames, filling gaps, insulating hot and cold water pipes, and filling holes and cracks.

APPLICATIONS

Before application, shake the can thoroughly approximately 20-25 times. Attach the application nozzle or gun to the valve. The application surface should be free of dirt, dust, and oil. To accelerate the reaction and achieve the best results, the surface should be moist. Turn the can upside down before use. Keep in mind that foam volume tends to expand.



TECHNICAL DATA

| | |
|---------------------------------|-------------------------------------|
| Product Type | Polyurethane Prepolymer |
| Polymerization System | Moisture hardening |
| Density | 18±2 kg/m ³ (ASTM D1622) |
| Surface Drying (L 1cm) | 5-8 dk. (AST C1622) |
| Curing Time (L 1cm) | 10-15 dk. (ASTM C1620) |
| Fire Resistance | B3 (DIN 4102-1) |
| Compressive Strength | 35 kPa (DIN 53421) |
| Tensile Strength | 45,11 kPa (SO1926-79) |
| Color | Açık Sarı |
| Volumetric Yield | 30-45 L (ASTM C1536) |
| Dimensional Stability | <-5 % (ISO2796/86) |
| Optimum Application Temperature | min. 20°C max. +25°C |
| Temperature Resistance | -30°C and +80°C |
| Optimum Application Temperature | 5°C and +35°C |

Ral

Volume



Light Yellow 845 gr 12 Pcs

REUSABLE SAFETY VALVE FOAM

PROPERTIES

Selsil Safety Valve Foam is a superior-quality, moisture-curing, single-component, multi-purpose polyurethane assembly foam. Its patented, anti-block safety valve system and removable, special application adapter allow it to be reused for up to two months after initial application without leakage. This system, which offers easy and effective use, allows for convenient control of foam output. It can be stored in its original packaging in either a vertical or horizontal position without the risk of valve sticking.

APPLICATIONS

- It is a single component.
- It cures with atmospheric humidity.
- It provides excellent adhesion to many building materials such as wood, concrete, tile, metal, and aluminum (except polyethylene, silicone, and Teflon).
- It provides sound and heat insulation.
- It can be cut and painted after curing.
- It has very good filling (expansion) capacity.
- It can be closed with a safety valve after use, allowing it to be used again even weeks later.



TECHNICAL DATA

| | |
|---------------------------------|-------------------------------------|
| Product Type | Polyurethane Prepolymer |
| Polymerization System | Moisture hardening |
| Density | 23±3 kg/m ³ (ASTM D1622) |
| Surface Drying (L 1cm) | 8-10 dk. (AST C1622) |
| Curing Time (L 1cm) | 20-25 dk. (ASTM C1620) |
| Fire Resistance | B3 (DIN 4102-1) |
| Compressive Strength | 43,8 kPa (DIN 53421) |
| Tensile Strength | 80 kPa (SO1926-79) |
| Color | Mavi |
| Volumetric Yield | 30-45 L (ASTM C1536) |
| Dimensional Stability | <-5 % (ISO2796/86) |
| Optimum Application Temperature | min. 20°C max. +25°C |
| Temperature Resistance | -30°C ile +80°C |
| Optimum Application Temperature | 5°C ile +35°C |

Ral

Volume



Green 750 ml 16 Pcs

FILLING AND ADHESIVE

MEGA FOAM (GUN)

PROPERTIES

Selsil Mega Foam is a multi-purpose mounting foam that hardens with moisture and has a 65-liter volume after curing. It is used for fixing doors, window frames, and similar joinery, filling gaps, electrical installations, insulating hot and cold water pipes, and sealing gaps, holes, and cracks. Mega Foam provides excellent thermal insulation, sound absorption, and high aging resistance. It is also resistant to fungi and mold.

APPLICATIONS

- It is a single component.
- It cures with atmospheric humidity.
- It provides excellent adhesion to many building materials such as wood, concrete, tile, metal, and aluminum. (Except polyethylene, silicone, and Teflon.)
- It provides sound and heat insulation.
- It can be cut and painted after curing.
- It is easy to use when applied with a gun.
- It requires less cleaning.
- It allows for faster tube changes.



TECHNICAL DATA

| | |
|------------------------------------|-------------------------------------|
| Base | Polyurethane Prepolymer |
| Polymerization system | Moisture hardening |
| Specific gravity | 23±3 kg/m ³ (ASTM D1622) |
| Tack-free time (L 1cm) | 6 min (ASTM C1620) |
| Cutting time (L 1cm) | 15-30 min (ASTM C1620) |
| Fire resistance after crosslinking | B3 (DIN 4102-1) |
| Compression strength | 32,6 kPa (DIN 53421) |
| Tensile strength | 52,2 kPa (SO1926-79) |
| Color | Light yellow |
| Yield | 30-45 L (ASTM C1536) |
| Dimensional stability | -1,33 % (ISO 2796/86) |
| Can temperature | min. 20°C max. +25°C |
| Temperature resistance | -30°C to +80°C |
| Application temperature | 5°C to +35°C |

| Ral | Volume | |
|--------------|-------------------|--------|
| Light Yellow | 850 ml 1000 gr | 12 Pcs |

FOAM CLEANER

PROPERTIES

Selsil Spray Cleaner for Foam is a cleaner that removes fresh polyurethane foams from the spray guns after use. Cleans surfaces, clothing, door and window frames, and prevents hardening inside the dispensing guns.

- Specifically formulated for cleaning polyurethane foams.
- The cleaner is equipped with a valve to remove the foam from the adapter of the dispensing gun.
- Can be used in all positions.
- The propellant gas used is not harmful.

APPLICATIONS

- Screw the cleaner package tightly onto the gun and spray.
- When the period between applications is longer than a week, do not fit a new foam pack after removing the cleaner from the gun.
- It can also be used by means of the supplied spray nozzle.



TECHNICAL DATA

| | |
|-------------|---------------------|
| Base | Mixture of solvents |
| Consistency | Liquid |
| Appearance | Transparent |

| Ral | Volume | |
|-------|--------|--------|
| Clear | 500 ml | 12 Pcs |

ADHESIVES

Selsil[®]

MONTAGE

FIRE SEALANT

PROPERTIES

Selsil Fire Sealant is a mastic based on sodium silicate and with its special formulation it is designed to withstand up to 1500°C. Purpose-designed for sealing and assembling stoves, ovens, barbecues.

- Fast hardening.
- Low odor.
- Solvent free.
- No cracking

APPLICATIONS

Ideal for sealing and assembling stoves, ovens and barbecues.

Excellent adhesion to most porous building materials and metals



TECHNICAL DATA

| | |
|-------------------------|-------------------------------|
| Density | 1,90 ± 0,05 g/cm ³ |
| Appearance | Thixotropic Paste |
| Temperature Resistance | -30°C to +1500°C |
| Application temperature | +5°C to +35°C |

| | | |
|-------|--------|--------|
| Ral | Volume | |
| Black | 300 ml | 25 Pcs |

PU D4 EXPRESS ADHESIVE

PROPERTIES

Selsil Quick Mounting Adhesive is a fast-curing mono-component polyurethane adhesive. Has high water resistance and adhesion strength. Fast polymerization.

- Short pressing time.
- Transparent.
- Meets D4 specs according to DIN EN 204.
- Excellent resistance to chemical agents.
- Excellent resistance to humidity and atmospheric conditions.
- Shrink-free.
- Low odor emission.
- Can be used on slightly wet substrates.

APPLICATIONS

- Fixing and gluing of wooden elements to other porous and non-porous elements such as wood, metal, concrete, expanded polystyrene and other plastics.

- Furniture manufacture and boat building.
- Fixing of raised floor installations in combination with mechanical devices.
- All bonding applications that require high water resistance.



TECHNICAL DATA

| | |
|-------------------------|---|
| Chemical Base | Polyurethane prepolymer |
| Appearance | Thixotropic Paste/Transparent |
| Density | 1.15 ± 0.03 g/ml |
| Tack-free time | 5 - 10 min (At 23°C and %50) |
| Volume loss | 0 mm |
| Pressing time | 15 - 20 min |
| Temperature resistance | -40° C to + 90°C |
| Application temperature | + 5°C to + 35°C |
| Tensile Shear Strength | 8-9 N/mm ² (after 24 h) (DIN EN 204) >10N/mm ² (after 7 days) (DIN EN 204) |

| | | |
|-------|--------|--------|
| Ral | Volume | |
| Clear | 300 ml | 25 Pcs |

MONTAGE

MONTAGE KIT

PROPERTIES

Selsil Solvent Based Adhesive is a quick adhesive for panels and is also ideal for filling. Adhesive based on a synthetic rubber/resin mixture with high adhesion strength in a solvent environment. Particularly suitable for fixing materials such as wood, concrete, plastic, stone, friezes, brackets, cabinet covers, PVC, mounting panels, etc

APPLICATIONS

- Solvent-based formula: fast drying / high initial adhesive strength.
- Excellent adhesion strength: adheres to most common surfaces.
- Exceptional early setting properties, usable both in vertical and horizontal position.
- Formulations with high solids content and excellent non-shrinkage gap filling properties.
- Excellent resistance to external atmospheric agents, suitable for outdoor use.
- Product not suitable for expanded polystyrene, polypropylene, polyethylene and Teflon.



TECHNICAL DATA

| | |
|-------------------------|--|
| Base | Mixture of resins and rubber (solvent based) |
| Appearance | Beige paste |
| Density | 1.24 g/cm ³ |
| Tack-free time | < 30 seconds |
| Tensile strength | 5 N/mm ² |
| Volume loss | 27% |
| Application temperature | + 5°C / + 35°C |
| Temperature resistance | -40°C / + 90°C |

| Ral | Volume | |
|-------|--------|--------|
| Cream | 300 ml | 25 Pcs |

D3 WOOD GLUE

PROPERTIES

Selsil Vinyl+D3 is a ready-to-use, water-resistant vinyl adhesive for wood based on a homopolymer emulsion of polyvinyl acetate. Specially formulated to comply with EN 204 (D3 = Water resistant).

APPLICATIONS

- Suitable for bonding all types of wood, wooden products and flat laminates.
- Wood on wood, soft and hard panels, synthetic resin panels and synthetic chipboard panels.
- Suitable for fixing paper, cardboard, paper or PVC fabric, on wood and cardboard.
- Can also be used to bond outdoor wooden structures such as window frames and exterior doors.
- Particularly suitable for moisture-resistant bonding which must meet high demands.



TECHNICAL DATA

| | |
|------------------------|-----------------------------|
| Chemical Base | PVA |
| Appearance | Paste/White |
| Solid Content % | %40 |
| Viscosity | 9000 ± 18000 cPs @20°C |
| pH | 4-5 |
| Water resistance class | D3 (DIN EN204) |
| Adhesive Consumption | 100-200 g/m ² |
| Open Time | 5-10 minute (23 0C-50 % RH) |
| Working Time | 10-15 minute (23 0C-50% RH) |
| Total Curing Time | 24 h (minimum) |

| Ral | Volume | |
|-----|--------|--------|
| - | 500 gr | 12 Pcs |
| - | 1 kg | 12 Pcs |
| - | 5 kg | - |
| - | 10 kg | - |
| - | 20 kg | - |
| - | 30 kg | - |

EPOXIES

MULTI PURPOSE EPOXY PUTTY

PROPERTIES

Selsil Epoxy putty is a two-component epoxy adhesive; consist of Epoxy resin and Mercaptane Terminated Hardener (1-1). It is suitable for the application of filling cracks, holes; repairing of concrete surfaces, tanks, drums and containers.

- Excellent Adhesion
- Good Heat Resistant
- Good water resistance (Suitable to underwater applications)
- Excellent adhesion - wood to metal, wood to glass and wood to ceramic
- No shrinkage and volume loss



TECHNICAL DATA

| | |
|------------------------------|----------------------------|
| Base | Epoxy |
| Density (g/cm ³) | Resin 1,9 |
| Hardener | 15000 |
| Application temperature | +5°C to +35°C |
| Mixing ratio | 1: 1 |
| Final appearance | Gray |
| Initial curing time | 5-10 (at 23°C) |
| Cross-linking time | 24 hours (at 23°C) |
| Temperature of use | +5°C to + 35°C |
| Filling capacity | Good |
| Shore D | 75 ± 2 (After 7 Days) |
| Paintable | Yes (but confirm by tests) |
| Sandable | Yes |

Ral Volume

- 57 gr 12 Pcs

PLASTIC EPOXY PUTTY

PROPERTIES

Selsil Epoxy putty plastic is a two-component epoxy adhesive; consist of Epoxy resin and Mercaptane Terminated Hardener (1-1). It is suitable for the application of rigid and semi-flexible plastic, ABS, PVS and CPVC pipes, automotive bumpers, fiberglass parts, vinyl siding.



TECHNICAL DATA

| | |
|------------------------------|----------------------------|
| Base | Epoxy |
| Density (g/cm ³) | 1,9 |
| Application temperature | +5°C to +35°C |
| Mixing ratio | 1: 1 |
| Final appearance | Off White |
| initial curing time | 5-10 (at 23°C) |
| Cross-linking time | 24 (at 23°C) |
| Temperature of use | +5°C to + 35°C |
| Filling capacity | Good |
| Shore D | 75 ± 2 (After 7 Days) |
| Paintable | Yes (but confirm by tests) |
| Sandable | Yes |

Ral Volume

- 57 gr 12 Pcs

EPOXIES

WOOD EPOXY PUTTY

PROPERTIES

Selsil Epoxy putty wood is a two-component epoxy adhesive; consist of Epoxy resin and Mercaptane Terminated Hardener (1-1). It is suitable for the application rotted or damaged wood, repairs to doors, windows and furniture, exterior columns, windows frames, large cracks and major repairs.

- Excellent Adhesion
- Good Heat Resistant
- Good water resistance (Suitable to underwater applications)



STEEL EPOXY PUTTY

PROPERTIES

Selsil Epoxy putty steel is a two-component epoxy adhesive; consist of Epoxy resin and Mercaptane Terminated Hardener (1-1). It is suitable for the automotive and machine parts, exhaust systems, plumbing, stripped threads, rust damage, household repairs.

- Excellent Adhesion
- Good Heat Resistant
- Good water resistance (Suitable to underwater applications)



TECHNICAL DATA

| | |
|------------------------------|----------------------------|
| Base | Epoxy |
| Density (g/cm ³) | 1,9 |
| Application temperature | +5°C to +35°C |
| Mixing ratio | 1: 1 |
| Final appearance | Beige |
| Curing time | 5-10 (at 23°C) |
| Cross-linking time | 24 hours (at 23°C) |
| Temperature of use | +5°C to + 35°C |
| Filling capacity | Good |
| Shore D | 75 ± 2 (After 7 Days) |
| Paintable | Yes (but confirm by tests) |
| Sandable | Yes |

Ral Volume

- 57 gr 12 Pcs

TECHNICAL DATA

| | |
|------------------------------|----------------------------|
| Base | Epoxy |
| Density (g/cm ³) | 1,9 |
| Application temperature | +5°C to +35°C |
| Mixing ratio | 1: 1 |
| Final appearance | Gray |
| Initial curing time | 5-10 min (at 23°C) |
| Cross-linking time | 24 hours (at 23°C) |
| Temperature of use | +5°C to + 35°C |
| Filling capacity | Good |
| Shore D | 75 ± 2 (After 7 Days) |
| Paintable | Yes (but confirm by tests) |
| Sandable | Yes |

Ral Volume

- 57 gr 12 Pcs

EPOXIES

EPOXY ADHESIVE 5 MINUTES

PROPERTIES

Selsil Fast Setting Epoxy Adhesive is a two-component, solvent-free, fast-curing and extremely resistant multipurpose epoxy-based adhesive.

APPLICATIONS

- Bonding of wood, glass, crystal, ceramic, porcelain, marble, metal, fiberglass, leather, rubber, fabric and rigid plastic surfaces.
- Sealing of electrical components.
- Repair of furniture and household items, household materials. Not recommended for polyethylene, polypropylene, nylon, PTFE, plastics.



TECHNICAL DATA

| Base | Epoxy |
|------------------------------------|------------------------------|
| Density/Resin (g/cm ³) | Resin 1.17 g/cm ³ |
| Density/Hardener | 1,15 g/cm ³ |
| Viscosity/Resin (cPs) (25°C) | 11.500-13.500 |
| Viscosity/Hardener | 15000 |
| Application temperature | +20°C to +80°C |
| Mixing ratio | 1: 1 |
| Gel time | 4-10 min (at 23°C) |
| Total cure time | 24 hours (at 23°C) |
| Temperature of use | +5°C to + 35°C |
| Shore D | 80 ± 2 (After 7 Days) |

Ral Volume

- 28 gr 12 Pcs

WATERPROOF ADHESIVE 30 MINUTES

PROPERTIES

Selsil Waterproof is a fast cure two-component adhesive based on epoxy. Dispenses equal amounts of each component every time. Can be applied on ceramic, wood and some rubber types. (Not suitable for PP, PE and Teflon) After application should not be touched around 2 hours. Resistant to water, alkalis and diluted acid solutions. No color change, cracking or shrinkage during hardening period. Over paintable, can be sanded and drilled.

APPLICATIONS

- The surfaces must be clean and free from dust and grease.
- Dispense the components equally (1:1 ratio) and mix until a homogenous mixture is obtained.
- Apply adhesive to the both surfaces to be bonded as quickly as possible and adhere surfaces immediately.
- Keep the assembled parts from moving during cure and fix.



TECHNICAL DATA

| Base | Epoxy |
|------------------------------------|------------------------------|
| Density/Resin (g/cm ³) | Resin 1.17 g/cm ³ |
| Density/Hardener | 1,15 g/cm ³ |
| Viscosity/Resin (cPs) (25°C) | 11.500-13.500 |
| Viscosity/Hardener | 15000 |
| Application temperature | +20°C to +80°C |
| Mixing ratio | 1: 1 |
| Working time | 8-12 (at 23°C) |
| Cross-linking time | 16 hours (at 23°C) |
| Temperature of use | +5°C to + 35°C |
| Shore D | 83 ± 3 (After 7 Days) |

Ral Volume

- 28 gr 12 Pcs

EPOXIES

METAL ADHESIVE 5 MINUTES

PROPERTIES

Selsil Steel Epoxy Adhesive is a two-component, epoxy-based, solvent-free adhesive. Fast curing and extremely strong, which develops high strength. Its filling capacity makes this adhesive particularly suitable for rough surfaces

APPLICATIONS

- Bonding of metal, concrete, wood, glass and ceramic.
- Ideal for repairing machinery, appliances, tools, automotive components, pipes, etc.
- Fixing of bolts and screws in metal, concrete or stone, electrical components



TECHNICAL DATA

| Base | Epoxy |
|------------------------------------|------------------------------|
| Density/Resin (g/cm ³) | Resin 1.17 g/cm ³ |
| Density/Hardener | 1,15 g/cm ³ |
| Viscosity/Resin (cPs) (25°C) | 11.500-13.500 |
| Viscosity/Hardener | 15000 |
| Application temperature | +20°C to +80°C |
| Mixing ratio | 1: 1 |
| Gel time | 4-10 min (at 23°C) |
| Total cure time | 24 hours (at 23°C) |
| Temperature of use | +5°C to + 35°C |
| Shore D | 80 ± 2 (After 7 Days) |

Ral

Volume



-

28 gr

12 Pcs

PLASTIC WELDING

PROPERTIES

Selsil Plastic Welding -MMA set is a methylmethacrylate based adhesive suitable for general purpose bonding of a wide variety of materials. Can be applied on ceramic, wood, many rigid plastics, china tile, fiberglass, concrete and stone. (The product is not suitable for PE, PP.)

Two-component (Component A+ Component B)

- Excellent adhesion
- Good water resistance Resistant to chemicals

APPLICATIONS

- The surfaces must be clean and free from dust and grease.
- Dispense the components equally (1:1 ratio) and mix until a homogenous mixture is obtained.
- Apply adhesive to the both surfaces to be bonded as quickly as possible and adhere surfaces immediately.
- Keep the assembled parts from moving during cure and fix.



TECHNICAL DATA

| Base | Epoxy |
|------------------------------------|------------------------------|
| Density/Resin (g/cm ³) | Resin 0,97 g/cm ³ |
| Density/Hardener | 0,97 g/cm ³ |
| Viscosity/Resin (cPs) (25°C) | 120000-160000 cPs |
| Viscosity/Hardener | 150000-200000 cPs |
| Application temperature | +18°C to +25°C |
| Mixing ratio | 1: 1 |
| Working time | 4-7 (at 23°C) |
| Cross-linking time | 13-16 hours (at 23°C) |
| Temperature of use | +50°C to + 120°C |

Ral

Volume



-

28 gr

12 Pcs

CYANOACRYLATE

NINJA SUPER GLUE

PROPERTIES

Selsil Cyanoacrylate Glue is a super fast, fast setting and low viscosity glue, developed on the basis of cyanoacrylate adhesive. Ideal where extremely rapid polymerization and / or high penetration capacity is required.

- Strong grip in seconds.
- Resistant to petrol and oils.
- Resists sudden changes in temperature and atmospheric agents

APPLICATIONS

- Suitable for glass, copper, rubber, metals, ceramics, ABS, polystyrene, NBR, nitrile, nylon, phenol, polycarbonate, wood, chromium, cellulose, chloroprene, marble, aluminum, Bakelite, bronze, ceramic, rigid and soft PVC, steel, stainless steel and various types of other materials.



TECHNICAL DATA

| | |
|-------------------------|--|
| Glue | Ethyl cyanoacrylate |
| Form | Liquid gel |
| Color | Transparent |
| Application temperature | +5°C to +35°C |
| Density | 1,05±0,05 g/cm ³ ASTM D1875 |

| | Ral | Volume | |
|-------------------------------------|-------|--------|--------|
| <input checked="" type="checkbox"/> | Clear | 20 gr | 50 Pcs |

SUPER GLUE WITH ACTIVATOR

PROPERTIES

Selsil Cyanoacrylate Glue with Activator is a bonding kit consisting of a cyanoacrylate adhesive and activator. Bonds quickly within seconds. Thanks to its high viscosity formula it can also be used vertically without drippings or stains. The activator also enables and accelerates to bond porous surfaces.

APPLICATIONS

- Assembly and repair of parts in natural stone, marble, granite, wood, leather, metal and many other types of substrate.
- Ideal for those applications that require very quick bonding.



TECHNICAL DATA

| | |
|-------------------------|--|
| Glue | Ethyl cyanoacrylate |
| Form | Liquid gel |
| Color | Transparent |
| Application temperature | +5°C to +35°C |
| Density | 1,05±0,05 g/cm ³ ASTM D1875 |
| Activator | Solvent based |
| Form | Aerosol |
| Color | Transparent |
| Application temperature | +5°C to +35°C |

| | Ral | Volume | |
|-------------------------------------|-------|-----------------|--------|
| <input checked="" type="checkbox"/> | Clear | 100 ml + 25 gr | 72 Pcs |
| <input checked="" type="checkbox"/> | Clear | 200 ml + 50 gr | 25 Pcs |
| <input checked="" type="checkbox"/> | Clear | 400 ml + 100 gr | 25 Pcs |

MULTI-PURPOSE ADHESIVE SPRAY

PROPERTIES

Selsil Multi-Purpose Adhesive Spray eliminates drying time with its fast and aggressive adhesion. It is a multi-purpose, fast-drying, clear spray adhesive.

- It provides excellent adhesion to paper, cardboard, fabric, cushions, plastic, metal, wood, glass, fiber, felt, cork, and many other materials.
- It allows 15 to 30 seconds after application before bonding to surfaces.



TECHNICAL DATA

| | |
|------------|----------------|
| Form | AerosolClear |
| Appearance | Clear |
| Odor | Characteristic |

Volume 

400 ml 24 Pcs

EMERGENCY AID BAND

PROPERTIES

Selsil Emergency Aid Tape is a self-fusing silicone rescue tape. It contains no adhesives. It is flexible and strong. It is water and airtight, saltwater resistant, and electrically insulating. Selsil Help withstands temperatures from -54°C to 260°C. It is suitable for use with all types of materials and in all environments and is resistant to gasoline, oil, acids, and solvents.

- It stretches up to 300%. The more it is stretched, the tighter and stronger the result will be.
- It provides very high sealing when wrapped over each other.
- It begins to self-fuse in just a few seconds.
- It has an electrical insulation rating of 8000V.

APPLICATIONS

Suitable for hundreds of DIY repairs, including repairing hoses, insulating electrical wires, waterproofing joints, tool holders, tool handles and much more.



TECHNICAL DATA

| | |
|-------------------------|-------------------------|
| Product Type | Silicone |
| Appearance | Band |
| Color | Black |
| Application Temperature | Between -54°C and 260°C |
| Voltage Resistance | 950 PSI |

Ral

Volume



Black

3,66 m

8 Pcs

DIY

CONTACT ADHESIVE

PROPERTIES

Selsil Contact Adhesive is a solvent based, toluene free medium viscosity adhesive.

APPLICATIONS

Recommended for metal substrates, wood, rubber, most plastics and leather, cork, linoleum, hard PVC plaster, polyurethane foam and mineral wool panel laminate materials. It can be used on PVC, polystyrene, cellulose painted substrates. (Not suitable for PP, PE, and Teflon.)



CLEAR GLUE

PROPERTIES

Selsil Clear Glue 50g is a colourless, synthetic resin adhesive for general applications such as handcraft, home and office, modelling work, etc.

APPLICATIONS

Selsil Clear Adhesive bonds extremely well metal, wood, paper and leather (not suitable for leather clothing) when applied. Can also be applied to materials such as glass, ceramics and most plastics.



TECHNICAL DATA

| | |
|------------------------|---|
| Chemical Base | Resin based |
| Color | Yellow |
| Appearance | Liquid |
| Specific Gravity | 0,85 ± 0,05 g/ cm ³ |
| Viscosity | 3600±250 mPa.s |
| Open Time | 15-20 mins (depending on the ambient temperature) |
| Solid Content | 25±1 % |
| Temperature Resistance | 100 °C |

TECHNICAL DATA

| | |
|-------------------------|-------------------------------|
| Chemical Base | Polyvinyl acetate |
| Appearance | Clear |
| Odour | Ketone like odor |
| Density | 0,96 ± 0,02 g/cm ³ |
| Application Temperature | -5 °C to +35 °C |

| Ral | Volume | |
|---|--------|--------|
| <input checked="" type="checkbox"/> Clear | 20 gr | 50 Pcs |

| Ral | Volume | |
|---|-----------------|--------|
| <input checked="" type="checkbox"/> Clear | 100 ml + 25 gr | 72 Pcs |
| <input checked="" type="checkbox"/> Clear | 200 ml + 50 gr | 25 Pcs |
| <input checked="" type="checkbox"/> Clear | 400 ml + 100 gr | 25 Pcs |

HARD PVC ADHESIVES

P12 ADHESIVE FOR PVC PIPES

PROPERTIES

Selsil P12 Rigid PVC Adhesive is a single-component PVC adhesive based on stabilized synthetic resin and volatile solvents. It is used in the joints of pressure and non-pressure pipes made of PVC, such as drinking water, gas, and agricultural pipes.

APPLICATIONS

- Easy to apply.
- The material should be mixed thoroughly before use.
- Complete drying time is 10 minutes. (Ambient Temperature 23°C)
- Pipes should not be removed before the drying process is complete.
- Wait 8 hours before using the pipes and 24 hours for pressure tests.



TECHNICAL DATA

| | |
|-------------------------|-------------------------------|
| Product Type | Synthetic Resin |
| Color | Transparent |
| Application Temperature | Between -5°C and 35°C |
| Density | 0,92 ± 0,03 g/cm ³ |

| | Ral | Volume |  |
|-------------------------------------|-------|--------|---|
| <input checked="" type="checkbox"/> | Clear | 50 gr | 48 Pcs |
| | | 125 gr | 30 Pcs |

MARBLE AND GRANITE ADHESIVE

PROPERTIES

Selsil Marble and Granite Adhesive is a two-component adhesive based on unsaturated polyester resin that can be hardened with a hardener.

- Easy to apply.
- Maintains its color.
- Does not separate, crack, soften, or warp at temperatures between 200°C and 1000°C.
- Does not produce odor.
- Resistant to solvents, alkalis, and molten acids.

APPLICATIONS

It is used to bond materials such as marble, stone, ceramic, tiles, china, tile mosaic, terracotta, emery stones, concrete and wood to each other or to each other.



TECHNICAL DATA

| | |
|-------------------------|--------------------------------|
| Product Type | Synthetic Resin |
| Application Temperature | Between -5°C and 35°C |
| Density | 1,80±0,03 gr/cm ³ |
| Use Time | 1-3% hardener and 3-5 min. |
| Curing Time | 6-9 minutes with 1-3% hardener |
| Hardness | 95±5 Shore A (After 24 Hours) |

| Ral | Volume |  |
|---|---------|---|
|  Cream | 250 gr | 24 Pcs |
| | 1000 gr | 12 Pcs |

EPDM ADHESIVE

PROPERTIES

Selsil EPDM Adhesive is a single-component, easy-to-apply, oxime-based neutral silicone. It offers high performance and is formulated for filling, sealing, and membrane bonding in building materials. It offers strong adhesion. It is UV resistant and 100% silicone- and solvent-free. It offers low modulus and high elasticity.

APPLICATIONS

It is used in EPDM bonding applications, as well as moldings, copper, steel, and galvanized sheet metal gutters, and connection joints (walls, concrete, PVC, wood, glass). It is recommended to test the product on the desired surfaces before use.



TECHNICAL DATA

| | |
|-------------------------|----------------------------|
| Product Type | Silicone Polymer |
| Polymerization System | Nötr (Oxim) |
| Intensity | 1.33 ± 0.03 TS 781 ISO 758 |
| Hardness | 25-30 Shore A |
| Tensile Strength | >200 % |
| Tensile Strength | 1.2 N/mm2 |
| Flowing | 0 mm |
| Thermal Resistance | -50°C +150°C |
| Application Temperature | +5°C to+40°C |

Ral

Volume



Black

600 ml

20 Pcs

CHEMICAL ANCHORS

Selsil[®]

EPOXY BASED

PROPERTIES

Selsil Epoxy Based Chemical Anchor is a high performance vinyl ester based injection mortar for solid and hollow substrates with short curing times. Suitable for use on concrete, stone, hollow brick and hollow blocks in a wide range of applications.

APPLICATIONS

- Anchoring of heavy loads on stone and concrete.
- Repair of mortars and adhesive mortars on concrete components.
- Anchoring of bars, threaded collars, reinforcement bars, profiles etc.
- Medium load applications in hollow bricks.
- Fixing of wooden constructions, metal constructions, metal profiles, sanitary accessories, pipe connections, overhanging roofs, facades, walkways, cable trays, railings, stairs, doors, window frames.



POLYESTER BASED

PROPERTIES

Selsil Polyester Based Chemical Anchor is a general purpose polyester based injection resin for solid and hollow substrates with short curing times. Suitable for use in concrete, hollow brick and hollow concrete blocks.

APPLICATIONS

- Anchoring of heavy loads on stone and concrete. Threaded collars, anchoring or reinforcement of bars, profiles.
- Repair of mortars and adhesive mortars on concrete components.
- Medium load applications in hollow bricks.
- Fixing of wooden constructions, metal constructions, metal profiles, sanitary accessories, pipe connections, overhanging roofs, facades, walkways, cable trays, railings, stairs, doors, window frames.



TECHNICAL DATA

| | |
|-------------------------|---|
| Base | Epoxy |
| Color | Light gray/Beige (Component A) Dark gray (Component B) |
| Density | 1.65 ± 0.03 (Component A) 1.3 ± 0.03 (Component B) |
| Complete curing | 7 days |
| Application temperature | +5°C to +35°C |
| Temperature resistance | -30°C to +100°C |

TECHNICAL DATA

| | |
|-------------------------|---|
| Base | Polyester |
| Color | Light gray/Beige (Component A) Dark gray (Component B) |
| Density | 1.66 ± 0.03 (Component A) 1.3 ± 0.03 (Component B) |
| Complete curing | 7 days |
| Application temperature | +5°C to +35°C |
| Temperature resistance | -30°C to +100°C |

Ral Volume

- 300 ml 12 Pcs

Ral Volume

- 300 ml 12 Pcs

SPRAYS

Selsil[®]

TECHNICAL SPRAY

BRAKE CLEANER

PROPERTIES

Brake spray cleans dust, grease on all the brake parts in an efficient way. Cleans the dust on disc and drum With its efficient formula it cleans without disassembling the brake unit It helps to decrease voice causing from brake parts.

- Dries immediately
- Cleans deeply
- Can be applicable 360° It is not corrosive
- Leaves no chemical residue



TECHNICAL DATA

| | |
|------------|----------------|
| Form | Aerosol |
| Appearance | Clear |
| Odor | Characteristic |

Volume

500 ml 24 Pcs

LABEL REMOVER SPRAY

PROPERTIES

Selsil Label Remover has a special formulation for the quick and efficient removal of paper based pressure sensitive adhesive labels on different types of surfaces

- With its efficient formulation it cleans without leaving adhesive residue or scratching surface.
- Cleans deeply.
- It is not corrosive.
- Harmless to most surfaces.
- Does not contain CFC, halogenated solvent.



TECHNICAL DATA

| | |
|------------|---------|
| Form | Aerosol |
| Appearance | Clear |
| Odor | Limon |

Volume

200 ml 36 Pcs

RUST REMOVER

PROPERTIES

Selsil Spray Rust Remover is a non-silicone protective spray, effective lubricant, anti-rust. Thanks to its special formulation it is easily applied and penetrates into surfaces. Loosens rusted parts and provides a protective layer between metal surfaces. Decreases friction. Avoid friction-motivated squeaking and corrosion. Removes water and protects against moisture. Protects metal parts and surfaces from corrosion. Cleans dust/grease and adhesive particles on metal surfaces. With its non-silicone formulation, there will be no dirt on the surfaces.



TECHNICAL DATA

| | |
|------------|----------------|
| Form | Aerosol |
| Appearance | Clear |
| Odor | Characteristic |

Volume

200 ml 36 Pcs
400 ml 24 Pcs

LIQUID GREASE SPRAY

PROPERTIES

Selsil Liquid Grease Spray is a lubricating paste in spray form that helps reduce friction between metal and/or metal and plastic surfaces. Lubricates, reduces friction and wear, prevents rust and oxidation, hydrophobic, silicone-free formulation, can be applied in all directions (360°), thanks to its special formulation, it is easily applied and penetrates surfaces.



TECHNICAL DATA

| | |
|------------|----------------|
| Form | Aerosol |
| Appearance | Clear |
| Odor | Characteristic |

Volume

500 ml 24 Pcs

TECHNICAL SPRAY

SILICONE SPRAY

PROPERTIES

It is an aerosol spray based on transparent, lubricating and high quality silicone oil. Lubricates, reduces friction and wear, prevents rust and oxidation, is hydrophobic, provides effective insulation.



TECHNICAL DATA

| | |
|------------|-------------------------------|
| Form | Aerosol |
| Appearance | Clear liquid, slightly turbid |
| Odor | Characteristic |

Volume

| | |
|-------|--------|
| 500ml | 24 Pcs |
| 200ml | 36 Pcs |

ENGINE CLEANER

PROPERTIES

Selsil Engine Cleaner, has a unique cleaning efficiency with its solvent containing non-foaming formulation. It dissolves grease, oil and dirt on all types of engines.

- With its special formulation, it can be easily applied and penetrates in to the surfaces.
- Makes equipment run smoother and last longer.
- Cleans the dust/ grease and dirt on the engine surfaces.
- With its non-foaming formulation , there won't be dirt on the surfaces.



TECHNICAL DATA

| | |
|------------|----------------|
| Form | Aerosol |
| Appearance | Clear |
| Odor | Characteristic |

Volume

| | |
|-------|--------|
| 500ml | 24 Pcs |
| 200ml | 36 Pcs |

ZINC SPRAY

PROPERTIES

Permanently protects metal surfaces affected by cathodic corrosion. It offers fast drying and high adhesion capacity and with its special formulation, provides long-term protection. Good resistance to mechanical shocks. High quality technical spray. Economical and reliable. Adheres to a wide variety of metal surfaces. Quick drying.



TECHNICAL DATA

| | |
|--------------------|---|
| Form | Aerosol can containing solvent; alkyl-based resin |
| Color | Metallic gray |
| Odor | Characteristic |
| Application Temp. | 5°C to 35°C / (optimum 18°C-25°C) |
| Wet Film Thickness | <20 µm |
| Dry Film Thickness | <10 µm |
| Total Curing Time | <24 hr |

Volume

| | |
|-------|--------|
| 400ml | 24 Pcs |
|-------|--------|

GASKET CLEANER

PROPERTIES

Selsil Gasket is a general purpose cleaning spray to remove gas kets and gasket residue from any type of metal or plastic surface.

- Removes gaskets from aluminum easily
- Cleans deeply
- It is not corrosive
- Leaves no chemical residue
- Removes gaskets from small, difficult to reach areas



TECHNICAL DATA

| | |
|------------|----------------|
| Form | Aerosol |
| Appearance | Clear |
| Odor | Characteristic |

Volume

| | |
|-------|--------|
| 500ml | 24 Pcs |
|-------|--------|

TECHNICAL SPRAY

MAG WELDING SPRAY SILICONE FREE

PROPERTIES

Selsil Weld, is a special spray, avoids adherence of spatter to metal surfaces during welding and eliminates the need for chiselling, grinding or wire brushing after welding. Suitable for protecting nozzles, weld units and tools intended for arc-welding processes.

- Easy removal of welding spatter.
- It is not corrosive, protects from oxidation.
- Extended nozzle life, weld units and tools.
- Easy application.
- Very fast drying and non-flammable.



TECHNICAL DATA

| | |
|------------|----------------|
| Form | Aerosol |
| Appearance | Clear |
| Odor | Characteristic |
| Volume | |
| 400ml | 24 Pcs |

MOLD RELEASE SILICONE FREE

PROPERTIES

Selsil Mold Releaser is a special spray, used in mold making and casting, and works well with most liquid rubber and liquid plastic products. It will release mold rubbers (such as polyurethanes and polysulfides) from properly prepared models.

- Drying fast.
- Anti-Stick.
- Suitable in hot and cold molds.
- Colorless, odorless.
- Leaves no chemical residue.
- Silicone free.



TECHNICAL DATA

| | |
|------------|----------------|
| Form | Aerosol |
| Appearance | Clear |
| Odor | Characteristic |
| Volume | |
| 400ml | 24 Pcs |

WELDING SPRAY

PROPERTIES

Selsil Silicon Weld, is a special spray, avoids adherence of spatter to metal surfaces during welding and eliminates the need for chiselling, grinding or wire brushing after welding. Suitable for protecting nozzles, weld units and tools intended for arc-welding processes.

- Easy removal of welding spatter.
- It is not corrosive, protects from oxidation.
- Extended nozzle life, weld units and tools.
- Easy application.
- Very fast drying and non-flammable.



TECHNICAL DATA

| | |
|------------|----------------|
| Form | Aerosol |
| Appearance | Clear |
| Odor | Characteristic |
| Volume | |
| 400ml | 24 Pcs |

MOLD RELEASE

PROPERTIES

Selsil Mold MR Silicon Mold Release spray is a special product with high temperature resistance (+300°C) that prevents adhesion of the plastic or rubber raw material to the mold by forming a strong film layer on plastic injection machines.

- Forms a heat-resistant homogenous film layer on the surface, enabling molding several times.
- Resistant to high temperature up to +300°C.
- Leaves no stain on the product.
- Can be used for the manufacturing of parts from natural rubber, synthetic rubber, nitrile, neoprene, PP, HDPE, LDPE, PVC, etc. Can be used as an anti-adhesion agent in Paper and Textile manufacturing. Do not use for processes subject to post-dyeing. No disturbing odor.



TECHNICAL DATA

| | |
|------------|----------------|
| Form | Aerosol |
| Appearance | Clear |
| Odor | Characteristic |
| Volume | |
| 400ml | 24 Pcs |

TECHNICAL SPRAY

BELT DRESSING

PROPERTIES

Selsil Belt is a general purpose cleaning spray to extend belt life, prevent belt slippage.

- Avoids dirt and grime
- Hydrophobic
- Cleans deeply
- It is not corrosive
- Leaves no chemical residue
- Extends belt life and pulley bearing life



TECHNICAL DATA

| | |
|------------|----------------|
| Form | Aerosol |
| Appearance | Clear |
| Odor | Characteristic |

Volume

500 ml 24 Pcs

AIR CONDITIONING CLEANER

PROPERTIES

Selsil Air Conditioner Cleaning Spray cleans odours and deposits in the air conditioner system and environment. It ensures durable protection thanks to its special formula.

- Removes odours caused by the air conditioner.
- Removes tobacco smoke inside the car.
- No extra apparatuses and devices needed for application.



TECHNICAL DATA

| | |
|------------|---------|
| Form | Aerosol |
| Appearance | Clear |
| Odor | Limon |

Volume

150 ml 36 Pcs

CARBURETOR CLEANER

PROPERTIES

Selsil Carburetor Cleaner, has a unique cleaning efficiency with its solvent containing non-foaming formulation. It dissolves grease, oil and dirt on all types of engines.

- With its special formulation, it can be easily applied and penetrates in to the surfaces.
- Makes equipment run smoother and last longer.
- Cleans the dust/ grease and dirt on the engine surfaces.
- With its non-foaming formulation, there won't be dirt on the surfaces.



TECHNICAL DATA

| | |
|------------|---------|
| Form | Aerosol |
| Appearance | Clear |

Volume

500 ml 24 Pcs

COCKPIT SHINER

PROPERTIES

Selsil Cockpit spray cleans dust, grease on the car interiors (dashboard, cleans deeply

- Dries immediately and invisible
- It is not corrosive
- Leaves no chemical residue
- Cleans and shines for a like-new plastic trim and leather part.)
- Cleans the dust on different plastic parts
- With its efficient formula it appearance



TECHNICAL DATA

| | |
|------------|----------------|
| Form | Aerosol |
| Appearance | Clear |
| Odor | Characteristic |

Volume

200 ml 36 Pcs

TECHNICAL SPRAY

RUBBER SEALS RENOVATION

PROPERTIES

Selsil Rubber Seals Renovation Spray cleans dust, grease on all the rubber part, provides easy application and long lifetime.

- Decrease the voice coming from vehicle rubber part.
- Suitable all weather conditions, avoids adhesion of rubber parts on to the doors.
- Water resistant.
- Cleans deeply, It is not corrosive.
- Leaves no chemical residue.



TECHNICAL DATA

| | |
|------------|----------------|
| Form | Aerosol |
| Appearance | Clear |
| Odor | Characteristic |

Volume

200 ml 36 Pcs

SEAT BELT LUBRICANT CLEANER

PROPERTIES

Selsil Seat Belt spray is a special product with its lubricating effect increase the lifetime of the seat belts and provides easy usage.

- With its efficient formula it cleans deeply
- It is not corrosive
- Leaves no chemical residue
- Prevents the hardening of the seat belt



TECHNICAL DATA

| | |
|------------|----------------|
| Form | Aerosol |
| Appearance | Clear |
| Odor | Characteristic |

Volume

200 ml 36 Pcs

CONTACT CLEANER

PROPERTIES

Selsil Contact Cleaner is a general purpose cleaning spray for electrical contact applications.

- Avoids rust and corrosion
- Hydrophobic
- Dries immediately
- Cleans deeply
- Can be applicable 360 0
- It is not corrosive
- Leaves no chemical residue.



TECHNICAL DATA

| | |
|------------|----------------|
| Form | Aerosol |
| Appearance | Clear |
| Odor | Characteristic |

Volume

500 ml 36 Pcs

TAR & PITCH CLEANER

PROPERTIES

Selsil Tar, is a general purpose cleaning spray for removing dirt/grease from forming on your vehicle (doors, bumpers etc...)

- Avoids dirt on the body part of vehicle
- Cleans deeply
- It is not corrosive, protects from oxidation
- Easy application



TECHNICAL DATA

| | |
|------------|----------------|
| Form | Aerosol |
| Appearance | Clear |
| Odor | Characteristic |

Volume

500 ml 24 Pcs

200 ml 36 Pcs

TECHNICAL SPRAY

ETHER CAR STARTER

PROPERTIES

Selsil Ether Car Starter Spray is a special product helps to start engine during cold season times.

- Suitable for all engine types.
- It is not corrosive.
- Leaves no chemical residue.



TECHNICAL DATA

| | |
|------------|----------------|
| Form | Aerosol |
| Appearance | Clear |
| Odor | Characteristic |

Volume

200 ml 36 Pcs

ELECTRONIC CARD CLEANING SPRAY (OIL-FREE)

PROPERTIES

Selsil Electronic Board Cleaner is a clear spray protects circuits and electrical devices from moisture and chemicals.

- Easy application with its special design.
- With its special formulation, it provides fast drying.
- Resistance to moisture and chemicals.
- Resistant to chemicals
- With its non-siliconized formulation, there won't be dirt on the surfaces



TECHNICAL DATA

| | |
|------------|----------------|
| Form | Aerosol |
| Appearance | Clear |
| Odor | Characteristic |

Volume

500 ml 24 Pcs

200 ml 36 Pcs

MOLD CLEANER

PROPERTIES

Selsil Mold is a special cleaning spray to remove dirt and grease from engine blocks and composite molds.

- Removes residues (dust, grease, moisture.. etc) from surfaces easily and efficiently.
- It is not corrosive.
- Leaves no chemical residue.



TECHNICAL DATA

| | |
|------------|----------------|
| Form | Aerosol |
| Appearance | Clear |
| Odor | Characteristic |

Volume

400 ml 24 Pcs

TYRE SHINER

PROPERTIES

Selsil Tyre Shiner is a general purpose cleaning spray for removing dirt/ grease from forming on tyres.

- Avoids dirt on the rubber tyre part.
- Cleans deeply, provides shiny appearance.
- It is not corrosive, protects from oxidation.
- Extends tyre life.
- Easy application.



TECHNICAL DATA

| | |
|------------|----------------|
| Form | Aerosol |
| Appearance | Clear |
| Odor | Characteristic |

Volume

500 ml 24 Pcs

TECHNICAL SPRAY

RUST REMOVER PRO

PROPERTIES

Selsil Multipurpose Lubricant is a lubricating, protective, cleaning and loosening product for general maintenance applications. Lubricates, protects, removes dirt and grease, cleans, loosens rusty / oxidized parts and is hydrophobic. Non-silicone formulation. Removes rust and can be used in all positions



TECHNICAL DATA

| | |
|------------|----------------|
| Form | Aerosol |
| Appearance | Clear |
| Odor | Characteristic |
| Volume | |
| 200 ml | 36 Pcs |
| 400 ml | 24 Pcs |

PRO COBRA HEAD

PROPERTIES

Selsil PRO is a general-purpose maintenance spray that, thanks to its special formula, simultaneously provides lubricating, protective, and cleaning properties. Selsil Rust Remover PRO is ideal for loosening stuck parts in small motor vehicles (motorcycles, bicycles), and household appliances/applications (doors and electrical appliances). This silicone-free formula removes rust and can be used in all positions.



TECHNICAL DATA

| | |
|------------|----------------|
| Form | Aerosol |
| Appearance | Clear |
| Odor | Characteristic |
| Volume | |
| 200 ml | 36 Pcs |
| 400 ml | 24 Pcs |

NON-FLAMMABLE INDUSTRIAL CLEANING SPRAY

PROPERTIES

Non-FLM Industrial Cleaner Spray is a high-performance, non-flammable, solvent-based, and water-free general metal cleaning spray. Specially formulated with non-flammable components, it quickly and effectively removes tough grease, oil, dirt, rust residues, adhesives, and other stubborn contaminants from metal surfaces.



TECHNICAL DATA

| Property | Value |
|---------------------------|-------------------------|
| Appearance | Clear, colorless liquid |
| Odor | Characteristic solvent |
| pH Value | Not applicable |
| Flash Point | Non-flammable |
| Auto-ignition Temperature | Non-flammable |
| Explosion Limits | Not applicable |
| Boiling Point | >95 °C |
| Vapor Pressure (25°C) | 103.8 mmHg |
| Solubility in Water | Insoluble |
| Solubility in Oil | High |
| Viscosity (25 °C) | 0.77 mPa·s |
| Density (20 °C) | 1.57 g/cm ³ |
| Amount | 500 ml |

| | |
|--------|--------|
| Volume | |
| 500 ml | 24 Pcs |

ACRYLIC PAINT

SPRAY GAS

PROPERTIES

The Empty Gas Can is a solvent-based gas spray, filled with propellant and specially added solvents, ready for paint addition. Highly efficient, pressure-resistant, and optimally performing, it delivers professional-quality results. It's suitable for use with all solvent-based paints and is suitable for filling in all machines.



TECHNICAL DATA

Form Aerosol

Appearance Clear

Odor Mixture

Volume 

400 ml 12 Pcs

FLUORESCENT PAINT

PROPERTIES

Selsil Rainbow Colors is an acrylic, solvent-based spray paint specifically designed for decorative and protective purposes in indoor and outdoor spaces. It can be used safely on surfaces such as wood, metal, ceramic, plastic, concrete, paper, fabric, glass, and cardboard.



TECHNICAL DATA

Form Aerosol

Appearance Clear

Odor Mixture

Volume 

400 ml 12 Pcs

FLUORESCENT PAINTS



FLUORESCENT
RED
TAB-441



FLUORESCENT
PINK
TAB-439



FLUORESCENT
PURPLE
TAB-436



FLUORESCENT
YELLOW
TAB-437



FLUORESCENT
GREEN
TAB-438

ACRYLIC PAINT

COLORS SPRAY PAINT

PROPERTIES

Selsil Rainbow Colors is an acrylic and solvent based spray paint, specially developed to meet the needs of interior and exterior decoration for decoration and protection purposes. With its special formulation can be used in wood, metal, plastic, concrete, paper, glass and cartoon surfaces.



TECHNICAL DATA

| | |
|-------------------------|---|
| Form | Solvent-based aerosol, modified acrylic resin |
| Odor | Characteristic |
| Dry to the Touch | 5-10 min |
| Complete Drying | 24 hour |
| Dry Layer Thickness | <10 µm |
| Surface Temperature | 5°C and 20°C |
| Application Temperature | 10°C and +25°C, max. moisture 60% |

Volume

400 ml 12 Pcs

EFFECT PAINTS

| | | |
|---------------------------------------|--------------------------------------|-------------------------------|
| | | |
| ALUMINUM WHITE RAL 9006 TAB-424 | GRAY ALUMINUM RAL 9007 TAB-427 | COPPER RAL 8029 TAB-453 |

PRIMER PAINTS

| | |
|------------------------------------|-----------------------------------|
| | |
| GRAY PRIMER RAL 7042 TAB-461 | RED LINING RAL 3009 TAB-462 |

HEAT RESISTANT PAINTS

| | |
|--|--|
| | |
| GILDING GRAY 200°C RAL 9006 TAB-433 | BLACK 690°C HEAT RESISTANT RAL9005 TAB-432 |

ACRYLIC PAINTS

| | | | |
|--|---|---|--|
| | | | |
| BLACK MAT RAL9005 TAB-428 | BLACK GLOSSY RAL9005 TAB-429 | ANTHRACITE GRAY RAL7016 TAB-451 | ULTRAMARINE BLUE RAL5002 TAB-421 |
| | | | |
| GENTIAN BLUE RAL5010 TAB-443 | TRAFFIC BLUE RAL5017 TAB-420 | SKY BLUE RAL5015 TAB-448 | LIGHT BLUE RAL5012 TAB-422 |
| | | | |
| MOSS GREEN RAL6005 TAB-412 | LEAF GREEN RAL 6002 TAB-413 | GRASS GREEN RAL 6010 TAB-414 | LIGHT GREEN RAL 6018 TAB-415 |
| | | | |
| MELON YELLOW RAL 1028 TAB-410 | TRAFFIC YELLOW RAL 1023 TAB-409 | SULPHUR YELLOW RAL 1016 TAB-447 | ORANGE RAL 2004 TAB-408 |
| | | | |
| SIGNAL ORANGE RAL 2010 TAB-444 | VERMILION ORANGE RAL 2002 TAB-416 | TRAFFIC RED RAL 3020 TAB-419 | FLAME RED RAL 3000 TAB-418 |
| | | | |
| CARMINE RED RAL 3002 TAB-417 | WINE RED RAL 3005 TAB-401 | CHOCOLATE BROWN RAL 8017 TAB-450 | CONCRETE GRAY RAL 7023 TAB-445 |
| | | | |
| SILVER GRAY RAL 7001 TAB-423 | WINDOW GRAY RAL 7040 TAB-449 | PEBBLE GRAY RAL 7032 TAB-426 | LIGHT GRAY RAL 7035 TAB-425 |
| | | | |
| GRAY WHITE RAL 9002 TAB-446 | OYSTER WHITE RAL 1013 TAB-403 | LIGHT IVORY RAL 1015 TAB-411 | PURE WHITE MAT RAL 9010 TAB-402 |
| | | | |
| PURE WHITE GLOSSY RAL 9010 TAB-405 | TRAFFIC WHITE RAL 9016 TAB-404 | REFRIGERATOR WHITE RAL 9301 TAB-407 | SIGNAL WHITE TAB-406 |
| | | | |
| CLEAR VARNISH TAB-431 | | | |

Selsil[®]

**GREAT JOB
GREAT SOLUTIONS**

Selsil[®]

**GREAT JOB
GREAT SOLUTIONS**

Selsil[®]

**GREAT JOB
GREAT SOLUTIONS**

Selsil[®]

SELSIL.COM